




ARO®

Chemical Compatibility Guide

INGERSOLL-RAND
FLUID PRODUCTS

Aro is pleased to present this selection guide to provide a convenient and informative reference point for pump selection.

This information was compiled from information provided by material suppliers and manufacturers.

The compatibility listings are intended as a guide only. We assume no liability for their accuracy on their use. The user should test under their own operating conditions to determine the suitability of any compound and material in a particular application.

THERMOPLASTIC ELASTOMERS (TPE's) verses THERMOSETTING RUBBER DIAPHRAGMS

Aro's direction has been to move toward replacement of traditional thermoset rubber diaphragms with thermoplastic elastomers (TPE). Examples of TPE's include: **Santoprene, Nitrile (TPE) and Hytrel.**

TPE's are manufactured using a plastic injection molding process where the resin, or diaphragm material, is melted and injected into a mold to produce the diaphragm. The advantages of this process includes:

Features

Diaphragm is molded to optimum shape
Homogenous part
High performance resins
Injection molded/tight process control

Benefits

Excellent flex life
No delamination failures
Chemical, abrasion and flex life
Low cost/consistent performance

Laboratory testing has shown:

Santoprene outperformed all rubber diaphragms except Buna in the mild abrasive fluids.
The Geolast diaphragm had equivalent life to the Buna diaphragms and was superior to the other rubbers compounds.
Teflon with the Santoprene backer exhibited the best flex life of all diaphragms during the test series.

Traditional thermoset includes: **Buna-N (TS), EPR, Neoprene, Viton**

Thermosets diaphragms are constructed by sandwiching (laminating) a layer of fabric reinforcement between two sheets of unvulcanized rubber. These are placed in a mold and compressed under heat and pressure to bond and vulcanite the rubber.


Limitations of the process includes:

Inclusion of fabric limits design flexibility to achieve optimum diaphragm shape.
Fabric does not remain centered between the two rubber sheets
Incomplete bonding can occur
Time/Labor intensive
Inconsistent quality
"Wicking" of fabric


Results

Lower flex life
Poor abrasion / chemical attack
Delamination
Expensive
Inconsistent life
Delamination / Leakage

Injection Mold Process



Thermoset Mold Process (Lamination)



THERMOPLASTIC COMPOUNDS (TPE)

Thermoplastic elastomeric (TPE) diaphragms are manufactured using an injection molding process. The process allows the part to be molded in the shape and configuration required of the diaphragm to provide excellent performance and life. The TPE resins used to manufacture the diaphragms exhibit excellent dimensional and tensile characteristics eliminating the fabric reinforcement. The following TPE's are used in ARO diaphragm pumps.

THERMOSET (TS)

These materials are manufactured from natural rubber and man made additives to enhance resistance to various fluids. Diaphragms are manufactured using a compression molding process. A nylon fabric mesh is molded in the diaphragm to add strength to the compound.

TEFLON®

The most chemically inert man made compound known. New diaphragm design and material processing have significantly improved flex life equivalent to or exceeding rubber compounds. A backer diaphragm is used to provide additional support.

(BUNA-N)										
COMPOUND		Color Code	Temperature Limits **	Flex Life	Abrasion Resistance Balls (Seats)	Acid Service	Caustic Service	Solvents Ketones/Acetates	Hydrocarbons Aromatic/Chlorinated	Petroleum/oils
TPE	SANTOPRENE (Backer)	Tan (Green)	-40° to 225°F	A	A	A	A	B	D	D
	HYTREL*	Cream	-20° to 150°F	A	A	C	B	B	C	A
	URETHANE*	Clear	+10° to 150°F	A	A	D	D	D	D	A
	NITRILE (TPE)	Black	-40° to 180°F	B	B	B	B	C	C	B
	TEFLON	White	+40° to 220°F	A	C	A	A	A	A	A
RUBBER	NEOPRENE	Green	0° to 200°F	B	B	C	C	D	D	B
	NITRILE (TS) (BUNA-N)	Red	+10° to 180°F	B	B	B	C	C	C	A
	VITON	Yellow	-40° to 350°F	C	B	A	A	B	A	A
	EPR / EPDM	Blue	-60° to 280°F	B	B	B	A	B	D	D

Rating

A = Excellent

B = Good

C = Fair


D = Poor

* Not Available in all models

**Maximum temperature limits are based on mechanical stress only. Certain chemicals can significantly reduce maximum safe operating temperature.

HALOGENATED SOLVENTS EXPLOSION HAZARD

Pump models containing aluminum wetted parts cannot be used with 111.-Trichloroethylene, Methylene Chloride or other Halogenated Hydrocarbon solvents which react and explode. Although manufactures of those solvents typically add inhibitors to prevent a reaction, there is no assurance that they will prevent a reaction under all conditions. Special caution should be exercised handling reclaimed or used solvents since the inhibitors are often degraded. Only Stainless Steel or Acetal or PVDF pumps should be used for these materials. Other examples of Halogenated Hydrocarbon Solvents (H.H.C.) include, but not limited to the following: Trichloroethane, Methyl Chloride, Carbon Tetrachloride, Chloroform Dichlorethylene.



NON-METALLICS

- ω **Polypropylene** - A general purpose low cost material having broad chemical resistance for use in a wide variety of chemical applications.
- Kynar (PVDF)** - A high performance fluoropolymer resin with excellent chemical resistance properties. Used for pumping aggressive chemicals at elevated temperature. Material also has excellent mechanical properties.
- Groundable Acetal** - An excellent material for use in solvent transfer applications. The material incorporates metallic fibers in the resin to render the material conductive to eliminate static charge build up and potential static discharge.

Non-Metallic Wet End Materials	Temperature Limits**	Acid Service	Caustic Service	Solvents Ketones/Acetates	Hydrocarbons Aromatic/Chlorinated
POLYPROPYLENE	+32° to 150°F	A	A	NR	NR
PVDF	+10° to 200°F	A	A	*	*
GROUNDABLE ACETAL	-20° to 180°F	D	D	A	A

Rating

A = Excellent
B = Good
C = Fair
D = Poor

* Check compatibility guide for part specific solvent or hydrocarbon.

**Maximum temperature is based on mechanical stress only.
Certain chemicals can significantly reduce maximum safe operating temperature.

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Edpm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Acetaldehyde	D	B	A	D	B	D	D	A	D	B	C	A	D	B	A	A	A
Acetamide (Ethanamide)	A	A	A	A	D	B	D	A	A	A	A/70	A	A/75	A	A	A	A
Acetate Solvents	D	B	A	D	D	D	D	A	D	B	B	A/70	A/70	A	D	A	A
Acetic Acid	C	B	A	C	D	C	C	A	C	A	B	D	A	B	D	A	A
Acetic Anhydride	D	A	A	D	C(B)	B	D	B	D	A	C	D	D	B	D	A	A
Acetone	D	B	A	D	C	D	D	A	D	A 122°F	D	B	D	A	A	A	A
Acetonitrile (Methyl Cyanide)	D	A/70	A	D	X	D	B	A	D	X	B/70	X	A/120	A	A	A	B
Acetophenone (Acetyl Benzene)	D	B	A	D	X	D	X	B	D	X	B/70	X	A/70	B	A	A	B
Acetyl Acetone	D	X	A	D	X	D	D	A	D	X	X	X	X	D	A	A	X
Acetyl Chloride	D	B 70°	A	D	D	D	D	D	B	X	D	X	A/120	D	A	B	A
Acetylene	A	X	A	A	A	B	D	A	A	X	D	A	A	A	A	A	A
Acetyl Salicylic Acid (Aspirin)	X	C	A	A	X	B	X	B	A	X	X	X	X	D	B	B	X
Acrolein (Acryaldehyde)	X	A	A	C	D	D	D	A	B	X	X	X	X	B	B	B	X
Acrylonitrile (Vinyl Cyanide)	D	D	A	D	D	D	D	D	C	X	B	X	A/70	A	A	A	A
Adipic Acid	B	B	A	A	D	A140	X	A	A	A	A	A/70	A	B	B	B	A
Aero Lubriplate	A	C	A	A	D	A	X	D	A	X	A	A	A	A	A	A	A
Aerosafe 2300	D	B	A	D	A	D	A	A	D	X	X	A	X	A	A	A	X
Aerosafe 2300W	D	B	A	D	A	D	D	A	D	X	X	A	X	A	A	A	X
Aeroshell 1AC	A	D	A	A	D	B	B	D	A	X	A	A	B	A	A	A	A
Aeroshell 7A Grease	A	D	A	A	D	B	D	D	A	X	X	A	X	A	A	A	X
Aeroshell 17 Grease	A	D	A	A	D	B	A	D	A	X	X	A	X	A	A	A	X
Aeroshell 750	C	D	A	B	D	D	A	D	A	X	X	A	X	A	A	A	X
Alcohol Amyl (1-Pentanol)	B	A	A	B	A	B	D	A	B	A	A	A	A	B/70	B	A	A
Alcohol Benzyl (Phenol Carbinol)	D	A	A	D	D	B	C	C	A	A	A/70	A/70	A	B/70	A	A	A
Alcohol Butyl (Butanol)	B	A	A	A	D	A	D	A	A	A	B	A	A	B	B	A	A
Alcohol Diacetone (Tyranon)	D	C	A	D	D	D	B	B	D	X	B	A	A/70	B	B	A	A
Alcohol Ethyl (Ethanol)	A	B	A	A	A	A	D	A	A	A	A	A	A	B/200	A	A	A
Alcohol Hexyl (1-Hexanol)	A	B	A	A	D	B	D	B	A	X	A/70	A	A	A	A	A	A
Alcohol Isobutyl (2-Methyl-Propanol)	C	A	A	C	B	A	D	B	A	X	A/70	A	A	B	C	A	A
Alcohol Isopropyl (2-Propanol)	C	B	A	C	A	B	D	B	A	X	A	A	A/150	B	C	A	A
Alcohol Methyl (Methanol)	A	A	A	A	A	A	D	B	D	A	A/120	A	A	B	A	A	A
Alcohol Octyl (Caprylic Alcohol)	X	B	A	B	D	B	D	A	A	X	X	A	X	A	A	A	A
Alcohol Propyl (Propanol)	A	A	A	A	D	A	D	B	A	C	A	A	A/120	A	A	A	A
Allyl Alcohol	A	A	A	A	D	A	B	A	B	A	A	X	A	B	A	A	A
Allyl Bromide	D	X	A	D	D	D	A	D	B	X	X	X	X	D	A	X	X
Allyl Chloride	C	X	A	B	D	D	D	D	B	A70	A	X	A	D	C	B	X
Alkazine	D	D	A	D	D	D	D	X	A	B	X	X	X	X	X	X	X
Almond Oil (Artificial)	D	C	A	D	D	D	D	B/70	D	X	X	X	X	X	X	X	X
Alum (Aluminum Potassium Sulfate)	A	A	A	A	D	A	D	A	A	A	A	A	A	C	D	B	B
Aluminum Acetate	X	A	A	B	X	B	D	A	D	X	A	A	X	A	D	B	B
Aluminum Ammonium Sulfate	A	B	A	A	X	A/170	X	A	A	X	A	X	A	X	X	X	X
Aluminum Bromide	B	B	A	A	D	A	D	A	A	X	X	X	A	X	X	X	X
Aluminum Chloride	A	A	A	A	B	A	B	A	A	A	A	B	A	B	D	C	A
Aluminum Fluoride	B	A	A	A	X	A	C/70	B	A	A	A	D	A	B	D	C	B
Aluminum Hydroxide	A	A	A	A	D	A	B	A	A	A	A	A	A	A	D	A	B
Aluminum Nitrate	A	A	A	A	X	A/70	C	A	A	X	A	B	A	B	D	A	B
Aluminum Phosphate	A	A	A	A	X	A	D	A	A	X	A	A	A	X	X	A	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytre	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Aluminum Potassium Sulfate (Alum)	A	A	A	A	D	A	D	A	A	A	A	A	A	C	D	B	B
Aluminum Sulfate (Sulphate)	A	A	A	A	(B)	A	B	A	A	A	A	B/70	A	A	D	A	A
Amines	D	A	A	D	D	D	D	C	D	A/70	B/120	C/70	X	A	D	A	B
Ammonia, Gas, Cold	B	A	A	A	D	A	B	A	D	X	B	A	D	X	X	X	X
Ammonia, Anhydrous	B	A	A	B	D	A	X	A	D	A/70	A/70	D	D	A/70	A	A	A
Ammonia Liquids	B	A	A	B	X	A	B	A	D	D	A/70	D	A	D	A	A	B
Ammonia Nitrate	A	A	A	A	X	C	B	A	D	X	A	B/70	A	C	A	A	B
Ammonium Acetate	A	A	A	A	D	A	D	A	A	A	A	C	X	B	A	X	X
Ammonium Bicarbonate	B	A	A	A	X	A	C	B	D	A	X	X	X	X	X	X	X
Ammonium Bifluoride	A	A	A	A	X	A	D	A	A	X	A	X	A	X	D	X	X
Ammonium Carbonate	C	A	A	B	X	A	A	A	A	A	A	D	A	B	B	B	B
Ammonium Casenite	X	A	A	X	X	A	X	X	X	X	X	A	X	X	X	A	X
Ammonium Chloride 1%	A	A	A	B	A/70	A	B/70	A	A	A	A	A	A	C	D	C	A
Ammonium Dichromate	B	A	A	A	X	A	X	A	X	X	X	X	X	A	A	X	X
Ammonium Diphosphate	X	A	A	A	D	A	X	A	A	X	X	X	X	X	X	X	X
Ammonium Fluoride	B	B	A	B	X	B	X	A	A	X	A	X	A	D	D	D	A
Ammonium Hydroxide	B	A	A	B	(B)	A	D	A	B	A/140	A	B	A	B	B	B	A
Ammonium Nitrate	A	A	A	A	X	A	A	A	A	A	A	B	A	B	A	A	A
Ammonium Nitrite	A	A	A	A	X	A	D	A	A	A	A/70	X	A	X	X	A	X
Ammonium Oxalate - 5% Sol.	B	A	A	A	X	A	X	A	X	A	X	B	X	X	D	A	A
Ammonium Persulfate Sol.	D	A	A	D	X	A	D	B	A	A/140	X	X	A	C	D	A	A
Ammonium Phosphate	A	A	A	A	B	A	B	A	A	B	A	B	A	B	D	A	A
Ammonium Sulfamate	A	A	A	A	B	A	A	A	A	X	X	X	X	X	X	X	X
Ammonium Sulfate	A	A	A	A	B	A	A	A	A	A	A	A	A	B	C	A	B
Ammonium Sulfide	X	X	A	A	X	A	B	A	D	X	X	X	X	X	X	X	X
Ammonium Sulfite	A	A	A	A	X	A	D	A	A	A	A	D	X	C	D	B	A
Ammonium Sulphate 1% - 5%	A	X	A	A	C	A	B	X	D	A	A	A	A	B	C	A	B
Ammonium Thiocyanate	X	X	A	A	X	A	X	A	A	A	X	X	A	C	C	A	A
Ammonium Thiosulfate	A	A	A	A	X	A	X	A	A	X	X	B	X	A	D	A	X
Ammonium Thiophosphate	A	A	A	A	D	A	X	A	A	X	X	X	X	X	X	X	X
Amyl Acetate (banana oil)	D	D	A	D	C	D	D	A	D	A	B	D	A/120	B	X	A	B
Amyl Alcohol	B	A	A	B	A	A	D	A	A	A	B	A	A	B	C	A	B
Amyl Borate	X	B	A	B	X	A	D	D	A	X	X	X	X	X	X	X	X
Amyl Chloride (Chloropentane)	D	C	A	D	D	D	C	D	A	D	D	A	A	D	A	A	B
Amyl Chloranaphthalene	C	C	A	B	X	D	D	D	A	X	X	X	X	X	X	X	X
Amyl Naphthalene	D	C	A	D	D	D	D	D	A	X	X	X	X	X	X	X	X
Amyl Phenol	X	C	A	D	X	X	X	X	A	X	X	X	X	A	A	A	A
Anderol, L-774 (Di-Ester)	X	X	A	A	X	D	D	D	A	X	X	X	X	X	X	X	X
L-826 (Di-Ester)	D	D	A	B	D	D	D	D	A	X	X	X	X	X	X	X	X
L-829 (Di-Ester)	D	D	A	B	D	D	D	D	A	X	X	X	X	X	X	X	X
ANG-25 (Glycerol Ester)	D	X	A	B	X	B	D	A	A	X	X	X	X	X	X	X	X
ANG-25 (Di-Ester Base) (TG7449)	D	D	A	B	X	D	D	D	A	X	X	X	X	X	X	X	X
Anhydrous Ammonia	B	A	A	D	D	D	D	A	D	X	A/70	D	D	B	D	A	A
Anhydrous Hydrazine	D	X	A	D	X	B	D	B	D	X	X	X	X	X	X	X	X
Anhydrous Hydrogen Fluoride	D	C	A	D	X	X	D	A	D	X	X	X	X	X	X	X	X
Aniline	D	A	A	D	C	D	D	D	D	C	A	A/70	A/70	C	C	A	B
Aniline Dyes	D	B	A	C	D	B	D	A	A	C	X	D	X	B	A	B	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytre	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Aniline Hydrochloride	D	A	A	C	X	D	D	B	B	X	D	X	A/100	D	D	D	X
Aniline Oil	D	C	A	D	D	D	D	B	C	X	X	X	X	B	A	A	B
Aniline Sulfite	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	C	X
Animal Oil (Lard Oil)	B	B	A	A	B	A	C	A	A	A	A	A	A	A	A	A	A
Animal Gelatin	B	B	A	A	X	A	A	A	A	X	X	X	X	X	X	A	X
AN-0-3 Grade M	B	B	A	A	D	D	B	B	A	X	X	X	X	X	X	X	X
AN-0-6	B	X	A	A	D	A	D	A	A	X	X	X	X	X	X	X	X
AN-0-366	B	X	A	A	D	D	D	C	A	X	X	X	X	X	X	X	X
Ansul Ether 161 or 181	D	D	A	C	D	X	B	C	D	X	X	X	X	X	X	X	X
Anthraquinone	D	D	A	C	D	D	B	C	D	X	X	X	X	B	B	B	A
Anti-freeze (Ethylene Glycol)	A	A	A	A	A70	A	B	A	A	A	A	B	A	B	B	A	A
Antimony Chloride	B	A	A	B	D	D	X	A	B	A	A	X	A	B	A	A	B
Antimony Trichloride	X	A	A	B	D	C	D	B	A	A	A	X	A	B	A	A	B
AN-VV-0-366b Hydr. Fluid	D	D	A	A	D	C	D	D	A	X	X	X	X	X	X	X	X
Aqua Regia (20% Nitric, 80% HCL)	D	D	A	D	D	D	D	B(140)	A/70	B	B/70	D	A/70	D	D	D	C
Argon	A	A	A	A	A	D	A	A	A	X	X	X	X	X	X	X	X
Aroclor	D	D	A	D	C	D	B/70	B	A	X	D	X	X	A	B	A	A
Aromatic Fuel 50%	X	C	A	A	X	D	D	D	A	X	X	X	X	X	X	X	X
Aromatic Hydrocarbons	D	C	A	D	C/70	D	D	D	A	X	D	A	X	A	A	A	X
Arsenic Acid	A	A	A	A	D	B	C	A	A	A	A	D	A	D	D	A	B
Arsenic Trichloride	B	B	A	A	D	A	X	D	A	X	X	D	X	D	D	D	B
Asorbic Acid	X	X	A	X	X	A	X	X	X	X	X	X	X	A	D	A	X
Askarel	C	D	A	B	D	D	D	D	A	X	X	X	X	X	X	A	X
Asphalt	B	B	A	B	(B)	C	B	D	A	X	A	B	A	A	B	A	X
Asphalt Emulsion	B	B	A	B	B	B	B	D	A	A	X	X	A	B	A	A	A
Asphalt Topping	B	B	A	B	B	B	B	D	A	A	D	D	D	A	A	A	A
ASTM Oil, No. 1	C	C	A	A	A	B	B	D	A	A	X	A	X	A	A	A	A
No. 2	X	C	A	A	A	B	D	D	A	A	X	A	X	A	A	A	A
No. 3	C	C	A	A	A	C	D	D	A	A	X	A	X	A	A	A	A
No. 4	X	X	A	B	D	D	D	D	A	A	X	A	X	A	A	A	A
B	B	C	A	D	A	D	D	D	A	X	X	X	X	A	A	A	A
C	C	C	A	B	A	D	D	D	A	X	X	X	X	A	A	A	A
ASTM Fererence Fuel A	B	B	A	A	A	B	D	D	A	X	X	X	X	A	A	A	A
Atlantic Dominion F	X	C	A	B	D	B	D	D	A	X	X	X	X	X	X	X	X
Aurex 903R (Mobile)	X	X	A	A	D	B	A	D	A	X	X	X	X	X	X	X	X
Automatic Transmission Fluid	X	D	A	A	A	B	B	D	A	X	X	A	X	A	A	A	A
Aviation Gasoline, Mil.	B	X	A	A	D	C	D	D	A	X	X	X	X	A	A	A	A
Bardol B	D	D	A	D	D	X	X	D	A	X	X	X	X	X	X	X	X
Barium Carbonate	A	A	A	A	X	A	B	A	A	X	A	A	A	D	A	A	A
Barium Chloride	A	A	A	A	X	A	A	A	A	A	A	A	A	D	D	B	A
Barium Cyanide	D	A	A	C	X	A	X	A	A	X	D	B	X	C	B	A	X
Barium Hydroxide (Barium Hydrate)	A	A	A	A	(B)	A	A	A	A	A	A	D	A	D	B	A	B
Barium Nitrate	A	A	A	A	X	A	B	A	A	A	A	B	A	B	A	A	A
Barium Sulfate	A	A	A	A	D	A	A	A	A	A	A	B	A	D	B	A	A
Barium Sulfide	A	A	A	A	X	A	A	A	A	B	A	A	A	D	D	B	A
Bayol D	D	D	A	D	X	A	X	D	A	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hydrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Bayol 35	D	D	A	D	X	A	X	D	A	X	X	X	X	X	X	X	X
Beef Extract	A	A	A	A	X	A	X	X	A	X	X	X	X	X	D	A	X
Benzaldehyde	D	D	A	D	B	D	D	A	D	A	D	A	A/70	A	A	A	A
Benzene (Benzol)	C	C	A	D	B	D	D	D	B	D	B	A	A	B	B	B	A
Benzene Sulfonic Acid	D	A	A	D	X	B	D	D	B	A	B/70	C	A	D	D	B	B
Benzyl Acetate	X	X	A	D	D	X	X	X	D	C	X	X	X	A	A	A	B
Benzyl Alcohol	D	D	A	D	C	C	D	C	A	A	A	X	A	A	A	A	B
Benzyl Benzoate	X	C	A	D	D	D	D	B	A	X	X	X	X	A	B	B	B
Benzyl Chloride (Chlorotoluene)	D	C	A	D	D	D	D	D	A	A	D	A	A	D	D	B	A
Benzoic Acid	D	A	A	D	D	D	D	B	A	A	A	B	A	B	D	B	B
Benzol (Benzene)	D	C	A	D	B	D	D	D	B	D	D	A	A/70	B	B	A	A
Bichloride of Mercury	B	B	A	A	X	A	A/70	A	A	X	X	X	X	X	X	X	X
Biphenyl (Diphenyl)	D	D	A	D	X	D	D	D	A	X	X	X	X	A	A	X	X
Bismuth Subcarbonate	X	D	A	A	D	D	D	A	X	X	X	X	X	X	X	X	X
Black Point 77	X	X	A	A	X	C	C/70	A	A	X	X	X	X	X	X	B	X
Black Sulphate Liquor	X	X	A	B	B	B	D	B	B	X	X	X	A/175	C	B	A	B
Blast Furnace Gas	X	A	A	D	B	D	D	D	A	A	X	D	X	X	X	X	X
Bleach Solutions (Water, Chlorine)	D	B	A	D	C	D	D	A	B	B	B	D	A	D	D	B	B
Blood (Meat Juices - Cold)	D	B	A	C	D	A	D	A	C	A	A	X	X	A	D	A	X
Borax (Sodium Borate)	A	A	A	B	A	A	A	A	A	A	A	A	A	C	A	A	A
Bordeaux Mixtures	B	A	A	A	B	A	D	A	A	A	X	X	X	D	C	A	A
Boric Acid	A	A	A	A	A/70	A	A/70	A	A	A	A	C	A	B	D	A	A
Boron Fluids (HEF)	C	D	A	B	D	D	A	D	A	X	X	X	X	X	X	X	X
Brake Fluid (Non-Petroleum)	D	A	A	C	D	B	A	A	D	A	D	X	X	A	A	A	A
Brine (Calcium Chloride)	A	A	A	A	B	B	B	A	A	A	A/70	A	A	C	D	A	A
Brewery Slop	X	A	A	A	D	A	A	A	A	X	X	X	X	X	A	A	X
Bromine	D	C	A	D	D	D	D	C	A	D	B/72	D	A/150	D	D	D	A
Bromine-Anhydrous	D	C	A	D	D	D	D	D	A	D	D	D	A/150	D	D	D	A
Bromine-Pentafluoride	D	D	A	D	X	D	D	D	D	X	X	X	X	X	X	X	X
Bromine Trifluoride	D	C	A	D	D	D	D	D	D	X	D	D	X	D	D	B	X
Bromine Water	D	B	A	D	D	D	D	D	B	D	D	D	A	D	D	B	X
Bromobenzene	D	D	A	D	D	D	D	D	B	D	D	D	A	D	B	B	B
Bromochloromethane	X	X	A	D	X	D	D	B	C	X	X	X	X	D	B	B	B
Bromochloro Trifluoromethane	X	D	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Bromotoluene	X	X	A	D	X	X	X	X	B	X	X	X	X	D	A	A	A
Bronzing Liquid	X	A	A	A/70	X	D	D	B/70	D	X	X	X	X	X	X	A	A
Bunker Oil	B	B	A	A/70	D	D	D	D	A	A	X	X	X	A	A	A	A
Butadiene (Monomer)	D	D	A	D	D	D	D	D	B	D	D	A	A	A	A	A	X
Butane (LPG) (Butyl Hydride)	A	D	A	A	A	B	D	D	A	D	B	A	A	A	A	A	A
Butanol (Butyl Alcohol)	B	B	A	A/70	B	A	D	A	A	A	B	A	A	B	B	A	A
Butter	A	B	A	A	B	B	A	A	A	A	A	A	A	A	D	A	X
Buttermilk	A	A	A	A	X	A	A	A	A	A	A	A	A	A	D	A	A
Butyl Acetate	B	B	A	D	C	D	D	D	D	A/70	B/70	B	A	A	A	A	A
Butyl Acetyl Ricinoleate	D	B	A	C	X	B/70	D	A/70	A/70	X	X	X	X	A	A	A	A
Butyl Acrylate	D	C	A	D	D	D	X	D	D	A	D	A	A/70	X	X	X	X
Butyl Alcohol (Butanol)	A	A	A	A	B	A	D	B	A	A	A/70	X	A	A	B	A	A
Butyl Amine (Aminobutane)	B	A	A	B	D	D	D	D	D	X	B	C	B/70	A	A	A	B

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytre	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Butyl Benzoate	X	C	A	D	X	D	D	A	A	X	X	A	X	B	B	B	B
Butyl Butyrate	X	C	A	D	D	D	X	A	X	X	X	X	X	A	A	A	A
Butyl Carbitol	D	B	A	D	X	C	D	A	C	X	X	A	X	X	X	X	X
Butyl Cellosolve	D	A	A	C	X	C	D	A	D	X	X	A	B	X	X	X	X
Butyl Chloride (Chlorobutane)	D	D	A	D	X	C	X	X	A	X	D	X	A	A/70	A	A	A
Butyl Ether (DiButyl Ether)	X	C	A	A	X	B	X	X	C	A	D	X	A/100	A	A	A	X
Butyl Oleate	D	C	A	D	X	D	X	B	A	X	X	A	X	X	X	X	X
Butyl Stearate	C	C	A/70	B	X	D	B	D	A	A	X	A	A/100	B	B	B	B
Butylene (Butene)	C	C	A	A	B	C	C	C	A	X	B	A	A	A	X	A	X
Butyraldehyde	D	C	A	D	D	D	D	C	D	X	D	A	B	A	A	A	A
Butyric Acid	D	A	A	D	B	D	D	B	B	A	A	D	A	A	D	B	A
Butyric Anhydride	X	A	A	C	X	X	X	X	X	D	X	X	X	A	A	A	A
Butyronitrile	X	X	A	D	D	D	X	A	C	X	X	X	X	X	X	X	X
Cadmium Sulfate (25% Concentration)	X	X	A	C	D	X	D	X	X	X	X	X	X	X	X	X	X
Calcium Acetate (Hydrate)	X	X	A	B	D	B	D	A	D	X	X	X	X	C	C	B	B
Calcium Acid Sulphate	X	X	A	C	X	C	X	B	D	X	X	X	X	X	X	X	X
Calcium Bisulphate	A	X	A	A	X	C	A	A	A	X	X	X	X	X	X	X	X
Calcium Bisulfide	A	D	A	A	B	A	A	D	A	X	A	A	A	C	D	B	A
Calcium Bisulfite	A	D	A	A	D	A	A	D	A	A	A	D	A	D	D	A	A
Calcium Carbonate (Chalk)	A	A	A	A	X	A	D	A	A	X	A	A	A	C	B	A	A
Calcium Chlorate	A	A	A	A	X	A	B	A	A	A	A	X	A	B	B	B	B
Calcium Chloride (Brine)	A	A	A	A	A	A	A	A	A	A	A	D	A	C	C	C	A
Calcium Hydrosulfide (Calcium Sulphydrate)	X	A	A	A	X	A	X	A	A	X	X	X	X	X	X	X	X
Calcium Hydroxide - 10% (Boiling)	A	A	A	A	B	A	A	A	A	D	A	A/150	A	C	A	A	A
Calcium Hypochlorite	C	A	A	C	B	D	D	A	A	A	A	A	A	C	D	A	A
Calcium Nitrate	C	A	A	B	X	B	D	B	A	X	A	D	A	B	C	B	B
Calcium Oxide (Unslaked Lime)	A	A	A	A	B	A	B	A	A	X	X	X	X	A	A	A	A
Calcium Silicate	X	X	A	A	X	A	X	A	A	X	X	X	X	A	B	A	A
Calcium Sulfate (Gypsum)	A	A	A	A	X	D	B	A	A	X	A	D	A	B	A	A	B
Calcium Sulfide	A	A	A	A	X	B	A	A	A	X	A/120	X	A	A	B	B	A
Calcium Sulfite	B	A	A	A	X	A	A	A	A	X	X	X	X	B	B	A	X
Calcium Thiosulfate	C	A	A	B	D	A	A	A	A	X	X	X	X	X	X	X	X
Calgon	A	A	A	A	D	A	D	A	A	X	A	A	X	X	D	A	X
Cane Juice	B	A	A	A	X	A	D	A	A	X	B/72	A	B	B	A	A	X
Cane Sugar Liquors	A	A	A	A	B	A	D	A	A	X	A	X	A	A	B	A	X
Capryl Alcohol (Octanol)	B	A	A	A	X	D	A	A	B	X	X	X	X	A	A	A	A
Caprylic Acid (Octanoic Acid)	C	A	A	C	X	X	X	A	A	X	X	X	A	A	X	A	A
Caprylic Aldehyde	X	X	A	D	X	X	X	X	D	X	X	X	X	X	X	X	X
Carbamate	D	A	A	C	X	B	D	B	A	X	X	X	X	X	X	X	X
Carbitol	C	B	A	B	X	B	D	B	A	X	C	X	A	B	B	B	X
Carbolic Acid (Phenol)	D	A	A	D	D	C	C	C	A	X	B	D	A/70	B	D	A	A
Carbon Bisulfide	D	D	A	D	B	D	C	D	A	D	D	B	A	A	B	B	B
Carbon Dioxide	B	A	A	A	C	A	C	A	B	C/70	A	A	A	A	D	A	A
Carbon Disulfide	D	D	A	D	C	D	C	D	A	D	D	B	A/70	A	B	B	B
Carbon Monoxide	A	A	A	A	A	B	A	C	A	X	B/70	B	A	A	A	A	A
Carbon Tetrachloride - Pure	D	D	A	C	D	D	A	D	A	C	A	A	A	D	C	A	A
Carbonated Beverages	A	A	A	A	X	A	B	A	A	X	A	X	A	C	D	A	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hydrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Carbonic Acid	B	A	A	A	C	A	C	A	A	B	A	A	A	D	B	A	
Casein	X	A	A	A	X	A	X	A	A	X	X	X	X	B	X	B	B
Casing Head Gas	X	X	A	A	X	A	X	X	X	X	X	X	X	X	X	X	X
Castor Oil	B	B	A	A	C	A	A	B	A	X	X	X	X	A	B	A	A
Catsup (Ketchup)	A	A	A	A	X	D	D	X	A	X	A	B	X	D	D	A	A
Cellosolve (Glycol Ethers)	D	C	A	D	D	D	D	B	D	X	A	A	A	B	B	B	A
Cellosolve, Acetate	D	A	A	D	D	D	D	B	D	C	A	A	A/120	B	B	A	A
Cellosolve, Butyl	D	C	A	D	D	D	D	B	D	X	X	A	B	X	X	X	X
Celluguard	B	B	A	A	X	A	D	A	A	X	X	X	X	X	X	X	X
Cellutherm 2505A	C	D	A	B	D	D	D	D	A	X	X	X	X	X	X	X	X
Cetane (Hexadecane)	B	D	A	A	D	B	D	D	A	X	X	X	X	X	X	X	X
China Wood Oil (Tung Oil)	B	B	A	A	B	A	C	D	A	A	A	A	A	A	A	A	A
Chloracetaldehyde	X	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X
Chlorate of Lime	D	D	A	C	D	D	D	A	A	A	X	X	X	X	X	X	X
Chlorbenzol (Conc. Pure)	D	D	A	D	X	D	X	D	D	X	X	X	X	X	X	X	X
Chlorextol	X	X	A	B	X	B	D	D	A	X	X	X	X	X	X	X	X
Chlorinated Lime - 35% (Bleach)	C	A	A	C	C	D	D	A	A	A	B	D	A	D	D	A	A
Chlorinated Water - Saturated	D	D	A	C	D	C	D	D	A	A	B	D	A	C	X	B	A
Chlorine, Dry	D	C	A	D	D	D	D	D	A/70	B	B	D	A	D	D	D	A
Chlorine, Wet	D	C	A	D	D	D	D	A	A	B	D	D	A	D	B	B	A
Chlorine, Anhydrous Liquid	D	D	A	D	D	D	D	D	A	C	D	D	A	D	D	D	A
Chlorine Dioxide	D	D	A	D	D	D	D	C	B	X	D	X	A	D	D	D	A
Chlorine Trifluoride	D	D	A	D	X	D	D	D	D	D	D	X	X	D	D	A	X
Chloroacetic Acid	C	D	A	D	X	D	D	B	D	X	X	X	X	X	X	X	X
Chloroacetone	D	C	A	D	D	C	D	D	B	X	D	B	X	D	B	B	B
Chlorobenzene	C	C	A	D	D	D	D	D	A	B	B	A	A/70	D	B/70	B	A
Chlorobromo Methane	D	D	A	D	D	D	D	B	A	A	D	B	X	D	B	B	X
Chlorobutadiene	D	C	A	D	D	D	D	D	A	X	D	X	X	D	B	A	B
Chlorodane	D	C	A	D	D	D	D	D	A	X	X	X	X	X	X	X	X
Chlorododecane	D	D	A	D	D	D	D	D	A	X	D	X	X	D	D	X	X
Chloroform	C	C	A	D	C	D	D	D	A	C	D	A	A	D	D	A	B
0 - Chloronaphthalene	D	D	A	D	D	D	D	D	A	C	D	X	A	D	B	B	B
1 - Chlorol 1 Nitro Ethane	D	C	A	D	D	D	D	D	D	X	D	X	X	D	X	X	X
Chlorosulfonic Acid (Dry)	C	C	A	D	C	D	D	C	C	D	C	D	C	D	D	D	B
Chlorosulfonic Acid (Wet)	D	D	A	D	D	D	D	D	D	D	C	D	C	D	D	D	B
Chlorotoluene	D	C	A	D	D	D	D	D	A	X	D	A	X	D	B	B	A
0 - Chlorphenol	C	C	A	D	X	D	D	D	B	X	X	B	A	C	C	A	A
Chromic Acid - 5%	D	A	A	D	D	D	D	A	A	A	A/70	D	A	C	D	A	A
Chromic Acid - 50%	D	A	A	D	D	D	D	C	A	A	B/140	D	A	C	D	B	A
Cider (Apple Juice)	B	A	A/122	A	D	A	D	A	A	A	A	A	X	B	D	A	A
Cinnamon Oil	X	C	A	X	X	C	X	X	X	D	X	X	X	X	D	A	X
Citric Acid - 5% Solution	A	A/70	A	A	B/70	A	A/70	A	A	A	A	C	A	C	D	A	A
Citric Oils	B	C	A	A	X	D	X	B	A	X	A	B	X	C	D	A	X
Citrus Pectin Liquor	B	X	A	A	B	A	C	X	C	D	X	X	X	X	X	A	X
Clove Oil	X	C	A	C	X	X	X	X	X	X	X	X	X	X	D	A	X
Coal Gas	X	X	A	D	B	A	B	A	A	X	X	X	X	X	X	X	X
Coal Tars	D	D	A	C	D	C	D	D	A	X	C	D	X	X	X	X	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Cobalt Chloride	A	A	A	A	X	A	D	C	A	X	A	X	X	D	D	X	X
Coca Cola Syrup	B	A	A	A	X	B	B	A	B	X	X	X	X	X	X	X	X
Coconut Oil (Coconut Butter)	B	B	A	A	X	C/140	C	B	A	A	X	X	X	B	A	A	X
Cod Liver Oil (Fish Oil)	X	C	A	A/70	X	B/70	A	A	A	X	X	X	X	A	D	A	X
Coffee	A	A	A	A	X	A	D	A	A	A	A	A	X	A	X	A	A
Coke Oven Gas	D	B	A	C	X	C	D	D	A	A	X	X	A	X	X	X	X
Coliche Liquors	B	B	A	B	X	A	X	B	X	X	X	X	X	X	X	X	X
Convelex 10	D	D	A	D	D	D	D	X	A	X	X	X	X	X	X	X	X
Coolanol (Monsanto)	B	D	X	A	X	B	D	D	A	X	X	A	A	D	D	C	B
Copper Acetate	X	A	A	B	D	B	D	A	D	X	X	A	A	D	D	C	B
Copper Chloride - 1%	A	A	A	A	A	A	D	A	A	A	A	A	A	D	D	D	B
Copper Cyanide	A	A	A	A	A	A	A	A	A	A	A	A	A	D	D	A	A
Copper Fluoborate	X	A	A	B	A	A	X	X	A	X	X	B	X	D	D	D	B
Copper Nitrate	B	A	A	A/140	A	A/140	B/70	A	A	A	A	A	A	D	D	A	A
Copper Sulfate - 5% Solution	A	A	A	A	A	A	A	A	A	A	A	D	A	D	D	A	A
Corn Oil	B	D	A	A	A	C	A	D	A	A	A	X	A	B	C	B	X
Cottonseed Oil	B	B	A	A	A/70	C	A/70	A/70	A	A/70	A	B	A	A	C	A	X
Creosols	D	C	A	D	X	D	D	D	A	D	D	B	A/150	B	C	A	B
Creosote, Coal Tar	D	D	A	B	D	D	D	D	A	X	D	D	X	B	B	B	B
Creosote, Wood	D	D	A	A	D	C	C	D	A	X	D	D	X	X	X	B	X
Cresylic Acid (Cresol)	D	B	A	D	D	D	D	D	A	D	C	D	A/150	C	A	A	B
Crotonaldehyde	D	B	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Crude Oil	C	C	A	B	B	B	D	D	A	A	B/150	D	A/120	A	A	A	B
Cumene (Isopropylbenzene)	D	D	A	D	X	D	D	D	A	A	X	X	X	B	B	B	B
Cutting Oil (Water Soluble)	C	D	A	C	X	D	A	D	A	A	X	X	X	A	A	A	A
Cutting Oil (Sulfur Base)	B	D	A	A	X	C	A	D	A	A	X	X	X	A	A	A	A
Cyclohexane	A	C	A	A	A	D	B	D	A	A/122	C/70	A	A	A	B	A	B
Cyclohexanol	C	D	A	B	X	A	B	C	A	A/170	B/70	A	A/150	C	B	B	A
Cyclohexanone	D	D	A	D	D	D	D	C	D	A/170	D	A	B/70	B	B	B	B
Cyanic Acid	D	B	A	C	X	D	D	A	D	X	X	D	X	X	D	A	X
P-Cymene	D	B	A	D	X	D	D	D	A	A	X	X	X	X	X	X	X
Decalin	D	C	A	D	X	D	D	D	A	C	B/120	X	A/175	X	X	X	X
Decanal	X	D	A	D	X	D	X	D	D	X	X	X	X	X	X	X	X
Decane	A	B	A	B	X	D	B	D	A	X	A/70	X	A	X	X	X	X
Decyl Alcohol (Decanol)	X	X	A	B	X	D	D	X	B	X	X	X	X	X	X	X	X
De-Ionized Water	A	A	A	A	A	A	X	A	A	A	A	X	A	A	C	A	A
Degreasing Fluid (Chlorinated)	D	D	A	D	X	D	A	D	A	X	X	X	X	X	X	X	X
Denatured Alcohol	A	B	A	A	X	A	D	A	B	X	A	A	A	A	A	A	A
Detergent Solutions	B	B	A	A	B	B	A	A	A	A	A	A	A	A	A	A	X
Developing Fluids (Photo)	X	A	A	A	D	A	D	B	A	A	X	A	X	X	D	A	A
Dextrose	A	A	A	A	B/140	B	A	A	A	X	A	X	A	A	D	A	A
Dextron	C	D	A	A	X	B	B	D	A	X	X	X	X	X	X	X	X
Diacetone Alcohol (Diacetol)	D	B	A	D	C	D	D	A	D	X	B	A	A/70	A	A	A	A
Diamylamine	X	B	A	B	X	D	D	A	D	X	X	X	X	X	X	X	X
Diazinon	D	D	A	C	D	C	D	D	B	X	X	X	X	X	X	X	X
Dibenzyl Ether	X	C	A	D	X	D	B	C	C	X	X	X	C	B	B	B	B
Dibenzyl Sebacate	D	C	A	D	X	D	B	B	B	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Dibromoethyl Benzene	D	C	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Dibutyl Amine	D	C	A	C	X	D	D	D	B	X	D	X	B	X	X	X	X
Dibutyl Ether	D	B	A	D	X	D	D	C	C	X	X	X	X	X	X	X	X
Dibutyl Phthalate	B	B	A	D	A	D	C	A	B	A	B	X	D	A	A	A	A
Dibutyl Sebacate	D	B	A	D	A	D	D	B	B	X	B/72	X	D	X	A	A	X
Dichloroacetic Acid	X	B	A	D	X	D	X	C	D	X	X	X	X	X	X	X	X
Dichloroethane	D	D	A	D	D	D	D	D	B	C	A	A	A/70	X	D	A	B
P-Dichlorobenzene	D	D	A	D	D	D	D	D	A	X	B	B	A/150	D	B	B	A
Dichlorobutane	X	X	A	B	X	D	D	D	A	X	X	X	X	D	B	B	X
Dichloroethyl Ether	X	X	A	D	X	X	X	X	X	X	X	X	X	B	X	X	X
Dichloro Isopropyl Ether	D	D	A	D	D	D	B	C	C	X	D	X	X	D	X	X	X
Dichloropentane	D	D	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Dicyclohexylamine	D	B	A	D	X	D	D	D	D	X	X	X	X	X	X	X	X
Diesel Oil (Fuel ASTM #2)	B	D	A	A	B	D	B	D	A	A/122	B/70	A	A	A	A	A	A
Di-Ester Lubricant Mil-L-7808	C	D	A	B	X	D	D	D	A	X	X	X	X	X	X	X	X
Di-Ester Synthetic Lubricants	D	D	A	D	D	D	D	D	A	X	X	X	X	A	A	A	A
Diethanol Amine	D	X	A	D	D	D	D	A	D	X	A	X	X	A	A	A	A
Diethyl Amine	D	C	A	C	X	B	C	B	D	X	A	X	A/70	B	D	B	X
Diethyl Aniline	D	B	A	D	X	D	D	B	C	X	A	X	A	X	X	X	X
Diethyl Benzene	D	C	A	D	X	D	D	D	A	D	X	X	X	X	X	X	X
Diethyl Carbonate	D	D	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Diethyl Ether	D	B	A	D	C	D	A	D	D	A/70	D	A	A/70	B	B	B	B
Diethyl Phthalate (DEP)	B	A	A	D	A	X	X	X	C	X	X	X	X	A	A	A	A
Diethyl Sebacate	B	B	A	D	A	D	D	B	A	X	A/120	X	A/120	A	A	A	A
Diethyl Sulfate	D	B	A	D	X	A	D	A	D	X	X	X	X	X	X	X	X
Diethylene Ether (Dioxane)	D	D	A	D	X	X	X	D	X	X	X	X	X	A	A	A	X
Diethylene Glycol	A	A	A	A	A	A	D	A	A	A	A	D	X	A	A	A	A
Diethylene Triamine	D	B	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Diffuorodibromomethane	D	B	A	D	D	D	D	B	X	X	X	X	X	X	X	X	X
Diisobutyl Ketone	D	B	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Diisobutylene	C	C	A	B	D	C	D	D	A	A/70	A/120	A	A	B	B	B	X
Diisodecyl Adipate (D10A)	X	X	A	D	X	X	X	X	C	X	X	X	X	X	X	X	X
Diisodecyl Phthalate (D10P)	X	X	A	D	X	D	X	A	C	X	X	X	X	X	X	X	X
Diisooctyl Adipate (D10A)	X	X	A	D	X	X	X	X	C	X	X	X	X	A	A	A	A
Diisooctyl Phthalate (D10P)	D	C	A	D	X	X	X	B	C	X	X	X	X	X	X	X	X
Diisooctyl Sebacate	D	D	A	C	X	D	D	C	B	X	X	X	X	X	X	X	X
Diisopropyl Amine	C	X	A	B	X	X	X	X	X	X	X	X	X	X	X	X	X
Diisopropyl Benzene	D	C	A	D	D	D	D	D	A	X	X	A	X	X	X	X	X
Diisopropyl Ketone	D	C	A	D	X	D	D	A	D	X	X	A	A	X	X	A	X
Dimethylaniline	D	B	A	D	X	D	D	B	C	A/70	A	D	A/70	A	X	X	B
Dimethyl Formamide	C	A	A	C	B	D	D	B	D	A/70	A/120	C	D	A	A	A	A
Dimethyl Phthalate	D	A	A	D	A	D	D	B	A	X	A	X	A/70	A	A	A	A
Dipentene	C	C	A	A	X	D	D	D	A	X	X	X	X	A	A	A	A
Diphenyl	D	C	A	D	X	D	D	D	A	X	X	X	A/120	A	A	A	A
Diphenyl Oxides	D	C	A	D	X	D	D	D	A	X	X	D	A	B	A	A	B
Dipropylamine	X	X	A	B	X	X	X	X	X	X	X	X	X	X	X	X	X
Dipropylene Glycol	A	A	A	A	X	X	X	X	A	X	A	X	A	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Dipropyl Ketone (Butyrene)	D	X	A	D	D	X	X	X	D	X	X	X	X	X	X	X	X
Dispersing Oil #10	D	X	A	D	X	D	X	D	C	X	X	X	X	A	A	A	A
Divinyl Benzene (DVB)	D	D	A	D	X	D	X	D	A	X	X	X	X	X	X	X	X
Dodecyl Benzene (Alkane)	D	X	A	D	X	X	X	X	A	X	X	X	X	A	A	A	X
Dow (Silicones)	A	A	A	A	B	A	A	A	A	X	X	X	X	A	X	X	X
Dowtherm A	D	D	A	D	B	D	D	D	A	X	B	X	X	C	B	A	X
Dowtherm E	D	D	X	D	B	D	D	D	A	X	B	X	X	X	X	X	X
Dry Cleaning Fluid	D	D	A	C	X	D	D	D	A	D	D	X	A	A	A	A	X
DTE Light Oil	B	D	B	A	B	B	D	D	A	A	X	X	X	X	X	X	X
Epichlorohydrin	D	B	A	D	D	D	D	C	D	X	A	A	C	D	A	A	A
Epsom Salts	A	A	A	A	X	A	X	A	A	A	A	B	A	A	A	A	B
Esam-6 Fluid	X	B	X	X	S	B	X	A	D	X	X	X	X	X	X	X	X
Esstic 42,43	A	D	X	A	D	B	B	D	A	X	X	X	X	X	X	X	X
Ethane	C	C	A	A	X	B/70	B/70	D	A	X	C	A	X	A	A	A	A
Ethanol (Ethyl Alcohol)	A	A	A	A	A	A	D	A	A	A	A	A	A	B	A	A	A
Ethanolamine (Aminoethanol)	B	A	A	B	X	B	C	B	D	X	B	D	C	B	B	A	B
Ethanol Chloride	D	B	A	D	X	D	X	C	B	X	X	X	X	X	X	X	X
Ethers	D	C	A	D	X	D	D	C	D	D	C	A	A/70	A	C	A	B
Ethyl Acetate	D	A	A	D	B	D	D	B	D	A/122	A	A/120	A	B	A	A	B
Ethyl Acetoacetate	D	B	A	D	D	D	D	A	D	A	X	A	A/70	A	A	A	A
Ethyl Acrylate	D	C	A	D	X	D	D	B	D	X	D	A	C	A	A	A	A
Ethylacrylic Acid	D	C	A	D	X	B	D	B	D	X	X	X	X	X	X	X	X
Ethyl Alcohol (Ethanol)	A	A	A	A	A	A	D	A	A/70	A	A	X	A	B	B	A	A
Ethyl Aluminum Dichloride	D	X	A	D	X	X	X	X	B	X	X	X	X	X	X	X	X
Ethyl Amine (Monoethylamine)	X	X	A	D	X	D	D	A	D	X	X	X	X	B	B	A	X
Ethyl Benzene	D	D	A	D	X	D	D	D	A	A/70	D	A	C	A	B	B	A
Ethyl Benzoate	D	C	A	D	X	D	D	D	A	X	B/70	A	X	A	A	A	A
Ethyl Bromide	C	X	A	B	X	D	D	D	A	X	D	X	X	A	A	A	X
Ethyl Butyl Acetate	D	X	A	D	X	X	X	X	D	X	X	X	X	X	X	X	X
Ethyl Butyl Alcohol	A	X	A	A	D	X	D	X	B	X	X	X	X	X	X	X	X
Ethyl Butyl Ketone	D	X	A	D	X	X	X	X	D	X	X	X	X	X	X	X	X
Ethyl Butyraldehyde	D	X	A	D	X	X	X	X	D	X	X	X	X	X	X	X	X
Ethyl Butyrate	D	X	A	D	X	D	X	D	C	C	B/70	X	X	B	A	A	A
Ethyl Caprylate	D	X	A	D	X	D	X	D	X	X	X	X	X	X	X	X	X
Ethyl Cellosolve	C	B	A	D	X	D	D	B	D	X	X	A	X	X	X	X	X
Ethyl Cellulose	B	A	A	B	B	B	B	B	D	X	X	A	X	B	A	B	B
Ethyl Chloride	C	D	A	A	C	D	C	A/140	A	X	D	A	A	D	C	A	B
Ethyl Chlorocarbonate	D	A	A	D	D	D	D	D	A	X	X	A	X	D	A	X	X
Ethyl Chloroformate	D	C	A	D	D	D	D	D	A	X	D	A	X	D	X	X	X
Ethyl Cyanide (Propionitrile)	D	X	A	D	X	B	X	A	D	X	X	X	X	X	X	X	X
Ethylcyclopentane	X	X	X	A	X	C	A	D	A	X	X	X	X	X	X	X	X
Ethyl Ether	D	D	A	D	X	D	D	D	D	D	C/70	A/70	B/170	B	B	A	B
Ethyl Formate	D	B	A	D	D	B	X	B	A	X	X	A	X	C	A	B	B
Ethyl Hexyl Acetate	X	X	A	D	D	X	X	X	D	X	X	X	X	X	X	X	X
Ethyl Hexyl Alcohol (Ethylhexanol)	A	A	A	A	D	A	D	A	A	X	X	X	X	A	A	A	A
Ethyl Iodide	X	X	A	D	X	D	X	C	B	X	X	X	X	X	X	X	X
Ethyl Isobutyrate	X	X	A	D	X	D	X	D	X	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Ethyl Mercaptan	D	C	A	D	X	D	A	D	B	X	X	X	X	B	A	B	B
Ethyl Oxalate	D	B	A	D	D	D	A	A	B	X	X	X	X	A	X	X	X
Ethyl Pentachlorobenzene	D	D	A	D	X	D	C	D	A	X	D	X	X	D	X	X	X
Ethyl Propionate	D	D	A	D	D	D	X	D	X	X	X	X	X	A	A	A	A
Ethyl Silicate	B	B	A	A	B	A	D	A	A	C	X	X	X	B	A	A	A
Ethyl Sulfate	D	B	A	D	X	A	D	A	D	X	X	X	X	X	X	D	X
Ethylene (Ethene)	B	C	A	A	D	C	B	D	A	X	X	A	X	A	A	A	X
Ethylene Chloride	D	D	A	D	C	D	D	C	C	C	C/70	A	A	B	C	A	B
Ethylene Chlorohydrin	D	C	A	D	D	B	D	B	A	X	D	C/70	A/70	B	B	B	X
Ethylene Diamine	B	A	A	B	X	A	D	A	D	A/70	A	A	B/70	A	A	A	C
Ethylene Dibromide	D	D	A	D	X	D	D	D	A	X	B/70	X	A	D	B	A	B
Ethylene Dichloride	C	C	A	D	C	D	D	D	B	C/70	D	A	A	B	A	A	A
Ethylene Glycol	A	A	A	A	A/70	A	B	A	A	A	A	B	A	B	B	A	A
Ethylene Oxide	A	A	A	D	A	D	D	B	D	C	C/125	A	A/70	D	C	A	X
Ethylene Trichloride	X	X	A	D	X	D	D	D	A	X	D	X	A	D	A	A	X
Ethylidene Chloride	D	D	A	D	X	D	X	D	X	X	X	X	X	D	B	A	B
Fatty Acids	B	B	A	B	D	B/70	D	D	A	A/140	B/140	B	A	B	D	A	A
Ferric Chloride	A	A	A	A/150	B/140	A/140	A/70	A/176	A/176	A/140	A	X	A	D	D	D	B
Ferric Hydroxide	B	B	A	B	X	B	X	B	B	X	X	X	X	X	X	A	B
Ferric Nitrate	A	A	A	A	D	B	A/70	A	A	X	A	A	A	D	D	A	A
Ferric Sulfate	A	A	A	A	A	A	A	A	A	A	A	B	A	D	D	A	A
Ferrous Chloride	B	A	A	B	A	A	D	A	A	A/70	A	B	A	D	D	D	B
Ferrous Sulfate (Copperas)	A	A	A	B	A	A	A	A	A	A	A	B/70	A	D	D	A	B
Fish Oil	A	B	A	A	B	B	B	D	A	A	X	X	X	X	X	X	X
Flourine (Anhydrous)	D	D	B	D	D	D	D	D	B	X	D	A	A/70	D	D	A	B
Flouboric Acid	A	A	A	A	D	A	D	A	A	A/140	A	X	A	D	D	B	A
Fluorobenzene	D	C	A	D	X	D	X	D	A	X	D	A	X	D	X	X	X
Fluorocarbon Oil	D	D	A	X	X	A	X	A	X	X	D	X	X	D	A	A	A
Fluorochloroethylene	D	C	A	D	X	D	X	D	A	X	X	X	X	X	X	X	X
Fluorolube (Fluoro Carbonoil)	X	X	A	A	D	A	X	A	B	X	D	X	X	A	A	A	A
Fluorinated Cyclic Ethers	D	D	A	D	X	D	X	A	A	X	X	X	X	X	X	X	X
Fluorosulfonic Acid	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Fluosilicic Acid	A	A	A	A	B	A	B	B	A/140	A/70°	A	X	A	D	D	B	B
Formaldehyde	A	A/70	A	C	B	B	D	A	A	A	A	A	A	A	D	A	B
Formamide	A	A	A	A	D	A	X	A	D	X	X	X	X	A	B	B	B
Formic Acid	A	A	A	D	B	D	D	B	B	A/140°	A	D	A	D	D	A	A
Freon 11	C	B	A	A	A	B	D	D	C	X	D	A	A	C	A	A	A
Freon 12	C	D	A	A	A	A	A/130	B	B	X	B	A	A	A	A	A	A
Freon 13	D	X	A	A	C	A	C/70	A	A	X	D	A	A	A	A	A	A
Freon 13BI	D	X	A	A	X	A	A	A	A	X	X	X	X	X	X	X	X
Freon 14	A	X	A	A	X	A	A/170	A	A	X	X	X	X	X	X	X	X
Freon 21	D	X	A	D	X	D	X	D	D	X	D	A	A	D	X	X	X
Freon 22	D	D	A	D	D	A	D	A	D	X	D	A	A	D	D	A	A
Freon 31	D	X	A	D	X	A	X	A	D	X	X	A	X	D	X	X	X
Freon 32	D	X	A	A	X	A	X	A	D	X	X	A	X	D	X	X	X
Freon 112	B	X	A	B	X	B	B/70	D	A	X	X	A	X	D	X	X	X
Freon 113	D	D	A	A	A	A	B	D	B	X	D	A	A	D	X	A	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Freon 114	B	X	A	A	A	A	A/70	D	A	X	D	A	A	C	X	A	X
Freon 114B2	X	X	A	A	X	A	X	D	B	X	X	X	X	X	X	X	X
Freon 142b	X	X	A	A	X	A	X	A	D	X	X	A	X	D	X	X	X
Freon 15	X	X	X	X	X	X	X	X	X	X	X	A	X	C	X	X	X
Freon 152a	X	X	A	A	X	A	X	A	D	X	X	A	X	D	X	X	X
Freon 218	X	X	A	A	X	A	X	X	A	X	X	A	X	D	X	X	X
Freon 502	X	X	A	B	D	A	X	A	B	X	X	A	X	D	X	X	X
Freon, BF	X	X	A	A	X	B	X	D	A	X	X	X	X	D	X	X	X
Freon C316	X	X	A	A	X	A	X	A	A	X	X	A	X	D	X	X	X
Freon C318	X	X	A	A	X	A	X	A	A	X	X	A	X	D	X	X	X
Freon K-142B	X	X	X	X	X	X	X	X	X	X	X	A	X	D	X	X	X
Freon K-152a	X	X	X	X	X	X	X	X	X	X	X	A	X	D	X	X	X
Freon, MF	X	X	A	A	A	D	D	D	D	X	X	X	X	D	X	X	X
Freon, PCA	X	X	X	A	X	A	A	D	B/70	X	X	X	X	D	X	X	X
Freon, TF	X	D	A	A	A	A	B	D	B	X	X	A	B	D	A	A	A
Freon T-WD602	X	X	A	B	X	B	A	B	A	X	X	X	X	D	X	X	X
Freon TMC	X	X	A	B	A	B	B	B	A	X	X	X	X	D	X	X	X
Freon T-P35	X	X	A	A	X	A	A	A	A	X	X	X	X	D	X	X	X
Freon TA	X	X	A	A	X	A	A	A	C	X	X	X	X	D	X	X	X
Freon TC	X	X	A	A	X	A	A	B	A	X	X	X	X	D	X	X	X
Fuel Oil	B	C	A	A	B	A	D	D	A	C	A	B	A	A	A	A	A
Fumaric Acid (Boletic Acid)	X	A	A	A	B	B	X	B	A	C	X	X	X	X	X	X	X
Fuming Sulphuric Acid (20%/50% Oleum)	D	X	A	D	D	D	D	D	A								
Furan (Furfuran)	D	A	A	D	X	D	X	D	D	X	C	X	D	A	A	A	X
Furfural (Ant Oil)	D	A	A	D	B	C	D	A	D	A/70°	D	B	B/120	A	B	A	B
Furfuryl Alcohol	D	C	A	D	B	D	D	B	D	X	X	X	B/100	A	A	A	A
Furyl Carbinol	D	X	A	D	X	D	D	B	D	X	X	X	X	X	X	X	X
Fusel Oil (Grain Oil)	X	X	A	A	X	B	C/70	A	A	X	X	X	X	X	X	X	X
Gallic Acid	D	B	A	B	D	B	D	B	A	A/140	A	X	A/70	A	D	B	B
Gasoline (Aviation)	D	C	A/170	A	A	D	C	D	A	X	D	A	A	X	X	X	X
Gasoline (Leaded)	C	C	A	A	A	D	C	D	A	X	D	A	A	A	A	A	A
Gasoline (Unleaded)	C	C	A	D	X	D	D	D	A	B	D	A	A	A	A	A	A
Gelatin	A	A	A	A	B	A	D	A	A	A	A	B	A	A	D	A	A
Galcial Acetic Acid	D	A	A	D	D	D	D	A	D	A	X	X	X	X	X	X	X
Glauber's Salt	X	X	A	A	B	A	A	B	A	A	X	X	X	X	X	X	X
Glucose (Corn Syrup)	A	A	A	A	B	A	A	A	A	A	A	A	A	A	B	A	A
Glue	D	A	A	A	A	A	A	A	A	A	A	B	A	B	A	A	A
Glycerin - Glycerol	A	A	A	A	A	A	D	A	A	A	A	A	A	A	B	A	A
Glycolic Acid	A	X	A	A	X	A	X	X	A	X	A	A	A/70	X	X	X	A
Grape Juice	A	A	X	A	X	A	D	A	A	A	A	B	A	B	D	A	X
Grapefruit Oil	X	A	A	A	X	D	X	X	A	X	X	X	X	X	D	A	X
Grease (Ester Base)	C	B	A	C	X	X	X	X	X	X	A	A	A	A	A	A	A
Grease (Petroleum Base)	A	D	A	A	A	D	A	D	A	X	A	A	A	A	A	A	A
Grease (Silicone Base)	A	B	A	A	X	X	X	X	X	X	A	A	A	A	A	A	A
Green Sulfate Liquor	B	A	A	B	D	B	A	A	A	A	A	X	X	B	C	A	B
Halothane	D	X	X	D	X	D	D	X	A	X	X	X	X	X	X	X	X
Halowax Oil	D	D	A	D	X	D	X	D	A	X	X	X	X	D	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Hannifin Lube A	A	D	X	A	X	A	A	D	A	X	X	X	X	X	X	X	X
Heavy Water	A	B	X	A	B	X	D	A	X	X	X	X	X	A	C	A	A
HEF - 2 (High Energy Fuel)	B	D	X	B/70	X	A	D	D	A	X	X	X	X	X	X	X	X
Helium	A	A	A	A	X	A	A	A	A	X	A	A	X	A	A	A	X
Heptane	B	C	A	A	B	A	B	D	A	A/122	/70	A	A	A	A	A	A
N-Hexaldehyde	D	C	A	D	D	A	B	A	D	A	X	X	X	A	A	A	X
Hexane	B	C	A	A	A	D	B	D	A	A/70°	B/70	A	A	A	A	A	A
Hexanol	A	C	A	A	D	B	D	A	A	X	A/70	A/70	X	A	A	A	A
Hexyl Alcohol	B	B	A	B	D	B	D	A	B	C	X	X	A	A	A	A	X
Hexylene Glycol	X	X	A	A	D	A	X	C/70	A	X	X	X	X	A	A	A	A
Hilo MS #1	D	X	X	D	D	D	B	A	D	X	X	X	X	X	X	X	X
Houghto-Safe 271 (Water & Glycol Base)	X	A	A	A	B	B	D	A	B	X	X	X	X	X	X	X	X
620 Water/Glycol	A	A	A	A	A	B	B	A	B	X	X	X	X	X	X	X	X
1010, Phosphate Ester	D	A	A	D	B	D	A	A	A	X	X	X	X	X	X	X	X
1055, Phosphate Ester	D	A	A	D	B	D	A	A	A	X	X	X	X	X	X	X	X
1120, Phosphate	D	A	A	D	B	D	A	A	A	X	X	X	X	X	X	X	X
5040 (Water/Oil Emulsion)	A	D	A	A	B	B	D	A	X	X	X	X	X	X	X	X	X
Hydraulic Oils (Petroleum)	A	D	A	A	A	B	X	D	A	A/70	D	B	X	A	A	A	A
Hydraulic, Oils (Synthetic)	A	D	A	D	A	D	B	D	A	A/70	D	B	X	A	A	A	A
Hydrazine (Diamine)	D	A	A	B	D	B	D	A	D	X	C	B	A/120	A	D	A	A
Hydrobromic Acid	D	B	A	D	X	D	X	A	X	A	B	D	A	D	D	D	A
Hydrochloric Acid 20%	D	A	A	D	D	D	B	A	A	A	A	D	A	D	D	D	A
Hydrochloric Acid 37%	D	B	A	B	D	D	D	B	A	A	A	D	A	D	D	D	A
Hydrocyanic Acid	D	A	A	B	D	B	D	A	A	A	A	D	A	A	D	A	A
Hydrofluoric Acid 20%	D	D	A	D	D	D	D	B	A	A	A*	D	A	D	D	D	D
50%	D	D	A	D	D	D	D	B	A	A	B/70	D	A	D	D	D	D
75%	D	D	A	D	D	D	D	D	D	X	B/70	D	A	D	D	D	D
Concentrated	D	D	A	D	D	D	D	D	D	X	D	D	A	D	D	D	D
Hydrofluosilicic Acid	D	B	A	B	B	B	D	A	A	A/70°	A	X	A	D	D	D	B
Hydrogen	A	A	A	A	A	A	A	B	A	X	X	X	X	X	X	X	X
Hydrogen Chloride Gas	B	B	A	D	X	B	X	A	A	X	A/140	X	A	D	A	A	A/125
Hydrogen Cyanide Gas	A	A	A	B	D	D	D	A	A	X	A	X	A	D	A	B	X
Hydrogen Fluoride	D	X	B/70	D	D	X	D	B/70	A	X	A/70	X	X	D	X	D	A
Hydrogen Peroxide	C	A	A	B	D	D	C	C	A	A	A/70	D	A/70	A	D	A	A
Hydrogen Sulfide Dry	D	A	A	A	A	A	A	A	D	A/70°	A	A	A	B	D	B	A
Hydrogen Sulfide Wet	D	A	A	D	A	A	D	A	D	A/70°	A	C	A	D	D	A	A
Hydrolube-Water/Ethylene Glycol	A	A/250	A	A/70	B/150	B/70	D	A/70	A/70	X	A	D	A	A	A	A	A
Hydroquinone	C	A	A	D	X	D	X	D	C	X	A	A	A	A	B	B	B
Hdyne	B	D	A	B	X	B	X	A	D	X	X	X	X	X	X	X	X
Hydroxyacetic Acid	D	A	A	D	X	D	D	A/70/100%	D	X	X	C	X	D	B	B	X
Hypochlorous Acid	D	A	A	D	X	D	D	B	A	X	A	D	A	D	D	D	A
Hypoid Grease (Parapoid 10-C)	B	X	A	B	X	D	D	D	C	X	X	A	X	X	X	X	X
Ink (Printers)	A	A	A	A	A	A	A	A	A	A	X	A	A	C	D	A	A
Iodine	B	A	A	B	B	D	D	B	A	A/70	A	A	A/150	D	D	D	B
Iodine Pentafluoride	D	B	A	D	X	D	D	D	D	D	X	X	X	X	X	X	X
Iodoform	B	B	A	X	X	B	D	B	A	X	X	X	A	B	A	B	D
Isoamyl Acetate	D	X	A	D	X	D	D	B	D	X	X	X	X	A	A	A	A

* Glass filled polypropylene NOT Recommended with Hydrofluoric acid.

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Isoamyl Alcohol	X	X	A	A	X	A	C	A	A	X	X	X	X	X	X	X	X
Isoamyl Butyrate	D	X	A	D	X	X	X	X	D	X	X	X	X	A	A	A	A
Isoamyl Chloride	D	X	A	D	X	D	X	D	A	X	X	X	X	D	X	X	X
Iso Butane	X	X	A	A	X	D	A	A/70	X	X	X	X	X	X	X	X	X
Iso Butyl Acetate	D	X	A	D	X	D	X	C/70	D	X	X	X	X	A	A	A	A
Isobutyl Alcohol	B	A	A	B/80	X	A/80	D	A/160	A/75	X	A/70	A	A	B	C	A	A
Isobutyl Amine	D	X	A	D	X	X	X	X	D	X	X	X	X	X	X	X	X
Isobutyl Chloride	D	X	A	D	X	X	X	X	B	X	X	X	X	D	B	B	A
Isobutyric Acid	D	X	A	D	X	B	X	A	X	X	X	X	X	A	X	X	X
Iso-Butyl N-Butane	D	X	A	D	D	X	D	X	B	X	X	X	X	X	X	X	X
Isocyanates	C	X	A	B	B	X	B	X	B	X	A	A	X	X	A	A	A
Isododecane	A	X	A	A/70	X	B/70	B/70	D	A/70	X	X	X	X	B	B	B	B
Isocatane	C	C	A	A	A/158	B	A	A/70	A	A/70°	A/120	X	A/70	A	A/70	A/70	A
Isopentane	A	X	A	A	X	D	B	D	A	X	X	X	X	X	X	X	X
Isophorone (Ketone)	D	B	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Isopropanol (Isopropyl Alcohol)	A	B	A	A/70	A/70	B/120	B	A/160	A/170	X	A	A	A	A	A	A	A
Isopropyl Acetate	D	B	A	D	C	D	D	B	D	C	A	A	X	B	A	A	B
Isopropyl Alcohol (Isopropanol)	A	B	A	A	A	B	D	A	A	A	A	A	A	A	A	A	A
Isopropyl Amine	D	X	A	D	X	X	X	X	D	X	X	X	X	X	A	A	X
Isopropyl Benzene (Cumene)	D	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X
Isopropyl Chloride	D	C	A	D	X	D	D	D	A	X	D	A	X	D	A	A	X
Isopropyl Ether	B	C	A	B	X	D	B	D	D	A/70°	B/70	A	X	A	X	A	A
JP-1	C	D	A	A	X	D	C	D	A	A	D	A	A	A	A	A	A
JP-2	C	C	A	A	X	D	C	D	A	A	D	A	A	A	A	A	A
JP-3 (Mil-J-5624)	C	C	A	A	X	D	C	D	A	A	A/70	A	A	A	A	A	A
JP-4 (Mil-J-5624)	A	D	A	A	A	D	C	D	A	A	A/70	A	A	A	A	A	A
JP-5 (Mil-J-5624)	C	C	A	A	X	D	B	D	A	A	A/70	A	A	A	A	A	A
JP-6 (Mil-J-25656)	C	C	A	A	X	D	C	D	A	A	D	A	A	A	A	A	A
JP-X (Mil-F-25604)	A	C	A	A	X	B	X	D	D	A	D	A	A	A	A	A	A
Kel F Liquids	X	X	A	A	X	X	X	A	B	X	X	X	X	X	X	X	X
Kerosene	A	C	A	A	A	X	B	X	A	B	B/72	A	A	A	A	A	B
Ketones	D	C	A	D	D	D	D	A	D	C	D	A	A/70	B	X	A	A
Keystone #87HX-Grease	X	X	A	A	X	D	A	D	A	A	X	X	X	X	X	X	X
Lactam-Amino Acids	X	X	A	D	X	B	X	B	D	X	X	X	X	X	X	X	X
Lacquers	D	C	A	D	D	D	D	D	D	A	C	A	D	A	C	A	A
Lacquer Solvents	A	C	A	D	B	D	D	D	D	A	C	A	D	A	B	A	X
Lactic Acid - 5% Solution	B	A	A	A	D	A	B	A	A	A	A	A	A/70	C	D	A	B
Lactol	X	X	A	A	X	D	X	X	A	X	D	A	X	A	A	A	A
Lard Oil (Hot)	X	B	A	A	B	A	C	B	A	A	B	AA	A	A	A	A	A
Latex	A	A	A	A	X	A	D	A	A	X	A	A	X	A	X	A	X
Lauryl Alcohol (N-Dodecanol)	X	X	A	A	X	X	D	X	B	X	X	X	X	A	A	A	A
Lavender Oil	B	B	A	B	X	D	X	D	A	X	X	X	X	X	X	X	X
Lead Acetate	B	A	A	B	X	B	D	A	A	A	A	A	A	D	A	B	B
Lead Chloride	X	X	A	A	X	B	X	A	A	X	A	X	A	D	X	B	B
Lead Nitrate	A	X	A	A	X	A	X	A	A	A/125	A	X	A	D	B	B	B
Lead Sulfamate	A	A	A	B	X	A	X	A	A	X	A	A	A	C	X	X	X
Lehigh X1169	X	X	A	A	X	B	A	D	A	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Lehigh X1170	X	X	A	A	X	B	A	D	A	X	X	X	X	X	X	X	X
Lemon Oil	X	C	A	A	X	C	X	C	A	X	X	X	X	A	X	A	X
Light Grease	X	X	A	A	X	D	A	D	A	X	X	A	X	X	X	X	X
Ligroin (Petroleum Ether or Benzene)	B	B	A	A	X	B	C	D	A	X	B/175	B	A	X	A	A	X
Lignin Liquor	X	X	A	A	X	A	D	D	A	X	X	X	X	X	X	A	X
Lime	A	A	A	A	A	A	B	A	A	X	B	X	A	C	A	A	X
Lime Bleach	B	A	A	A	X	B	X	A	A	X	B	X	X	D	X	A	X
Lime Slurries	A	A	A	A	X	A	B	C	D	X	X	X	X	B	X	B	X
Lime Sulfur	A	B	A	A	X	A	A	A	A	A	A	X	A	D	X	A	X
Lindol, Hydraulic Fluid	D	A	A	D	X	D	D	A	B	X	X	X	X	X	X	X	X
Limonene	D	X	A	D	X	D	X	D	A	X	X	X	X	X	X	X	X
Linoleic Acid	B	B	A	B	X	D	X	D	B	A	A	X	A	A	X	A	A
Linseed Oil	A	B	A	A	B	A	B	C	A	A/70°	A	A	A	A	A	A	A
Liquid Oxygen	D	X	A	D	X	D	D	D	D	X	X	X	X	X	X	X	X
Liquid Petroleum Gas (LPG)	D	C	A	A	B	C	C	D	A	X	D	A	X	X	X	X	A
Liquimoly	A	X	A	A	X	B	B/70	D	A	X	X	X	X	X	X	X	X
Lithium Bromide	A	X	A	A	X	D	D	A	A	X	X	X	A	X	A	X	X
Lithium Chloride	A	X	A	A	X	A	D	A	A	D	A/125	A	X	D	B	A	A
Lithium Hydroxide	D	X	A	D	X	D	D	A	C	D	A/70	X	X	D	B	B	B
Lubricating Oil Di-Ester	A	D	A	B	D	C	D	D	A	A	X	X	X	X	X	X	X
Petroleum Base	B	D	A	A	A	B/150	B/70	D	A	A	C	A	A	A	A	A	A
SAE 10, 20, 30, 40, 50	A	D	A	A	A	D	A	D	A	A	C	A	A	A	A	A	A
Lye Solutions	B	A	A	D	C	A	B	A	B	A	A	D	A/150	X	X	A	X
Lysol	B	X	A	B	X	B	X	X	X	X	X	X	X	X	X	X	X
Magnesium Bisulfite	C	X	A	B	X	B	X	X	X	X	X	X	X	X	X	X	X
Magnesium Carbonate	A	A	A	A	X	A	B	B	A	X	A	A	A	D	B	A	B
Magnesium Chloride	A	A	A	A	B	A	X	A	A	A	A	B	A	D	D	D	A
Magnesium Hydroxide (Milk of Magnesia)	A	A	A	A	B	A	A	A	A	A/70	A	A	A	D	B	A	A
Magnesium Nitrate	A	A	A	A	X	A	B	A	A	X	A	A	A	D	D	A	A
Magnesium Oxide	A	A	A	A	X	A	X	A	A	X	X	A	X	B	A	A	A
Magnesium Salts	A	A	A	A	X	A	A	A	A	X	X	X	X	X	X	X	X
Magnesium Sulfate	B	A	A	A	B	A	D	A	A	B/70	B	A	A	D	C	A	B
Magnesium Sulfite	B	A	A	A	X	A	X	A	A	X	X	X	X	X	X	X	X
Malathion	X	X	A	B	D	X	D	D	A	X	X	X	X	X	X	X	X
Maleic Acid	A	A	A	C	X	D	D	A	A	A/140	B	A	A	B	A	A	B
Maleic Anhydride	D	A	A	D	X	D	X	D	A	X	X	A	X	A	B	A	A
Malic Acid	B	A	A	A	X	B	X	D	A	X	B	A	A	B	D	A	B
Manganese Chloride	A	X	A	A	X	B	B	C	A	A/70	A	X	X	X	D	X	B
Malt Beverages	B	A	A	A	X	A	B	A	A	A	X	X	X	X	X	X	X
Maple Sugar Liquors (Sucrose)	A	A	A	A	X	A	D	A	A	X	X	X	X	X	X	X	X
Mash	A	A	X	A	X	A	A	X	X	X	X	A	X	X	X	A	X
Mayonnaise	A	A	A	A	X	A	D	D	A	X	A	A	A	D	D	A	A
MCS 312	D	X	A	D	X	D	X	D	A	X	X	X	X	X	X	X	X
MCS 352	D	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X
MCS 463	D	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X
Melamine Resins	C	B	A	C	X	D	D	A	A	X	X	A	X	X	X	D	A
Mercaptan	D	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Mercuric Chloride	A	A	A	A	B	A	A	A	A	A/70	A	B	A	D	D	D	B
Mercuric Cyanide	A	A	A	A	D	B	X	A	A	X	A	X	A	D	C	A	A
Mercurous Nitrate	B	X	A	B	X	B	X	A	A	X	A	X	A	D	B	B	B
Mercury	A	A	A	A	A	A	A	A	A	A	A	A	A	C	A	A	A
Mesityl Oxide	D	C	A	D	X	D	D	B	D	X	X	X	X	A	A	A	A
Methane	B	C	A	A	B	B	C	D	A	X	B	A	A	A	X	A	A
Methanol	A	A	A	A	A	A	D	A	D	A	A/120	A	A	B	X	A	A
Methyl Acetate	D	B	A	D	C	D	D	B	D	X	C	A	B	A	A	A	A
Methyl Acetoacetate	D	X	A	D	X	D	D	B	D	X	X	X	X	X	A	A	A
Methyl Acetone	D	B	A	C	X	D	X	A	D	X	D	A	D	A	A	A	A
Methyl Acrylate	D	D	A	D	X	D	D	B	D	X	X	A	B	X	A	A	X
Methyl Acrylic Acid	X	A	A	D	X	C	D	B	C	X	X	A	X	X	X	X	X
Methyl Alcohol	A	A	A	A	A	C	D	A	C	A/70°	A	A	A	B	A	B	A
Methyl Amine	B	X	A	B	X	C	X	A	C	X	X	A	C	B	A	A	B
Methyl Amyl Alcohol	B	X	A	A	X	D	X	X	C	X	X	X	X	A	A	A	A
Methyl Aniline	D	X	A	D	X	B	D	D	B	X	X	X	X	X	X	X	X
Methyl Benzoate	D	X	A	D	X	A	D	D	A	X	X	X	X	X	X	X	X
Methyl Bromide	B	D	A	B	X	A	D	D	A	X	D	A	A	D	A	A	B
Methyl Butyl Ketone	D	C	A	D	X	D	D	A	D	X	D	A	D	A	X	A	X
Methyl Butyrate	D	X	A	D	X	D	X	D	X	X	X	X	X	A	A	A	A
Methyl Carbonate	D	X	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Methyl Cellosolve	C	B	A	C	X	B	D	B	D	X	B	A	A	A	C	X	X
Methyl Cellulose	B	X	A	B	X	B	B/70	B	D	X	X	X	X	X	X	X	X
Methyl Chloride	D	D	A	D	D	D	D	D	B	X	D	A	A	D	D	A	B
Methyl Chloroformate	D	X	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Methyl Cyanide	C	X	A	C	X	A	X	A	D	X	X	X	X	X	X	X	X
Methyl Cyclopentane	D	C	A	D	X	D	D	X	A	A	X	A	X	X	X	X	X
Methyl D-Bromide	D	X	A	D	X	D	D	X	A	X	X	X	X	X	X	X	X
Methyl Dichloride	D	D	A	D	X	D	X	D	A	X	D	A	D	D	X	X	X
Methyl Ether	X	X	A	A	X	C	X	A	A	X	X	X	X	X	X	X	X
Methyl Ethyl Ketone (MEK)	B	B	A	D	B	D	D	A	D	A/70	C/125	B	D	A	A	A	A
Methyl Formate	D	B	A	D	X	B	D	B	D	X	X	A	X	A	B	B	X
Methyl Hexane	X	X	A	A	X	B	X	D	A	X	X	X	X	X	X	X	X
Methyl Iodide	D	X	A	D	X	D	X	A	X	X	X	X	X	D	A	A	A
Methyl Isopropyl Ketone	D	C	A	D	X	D	D	C	D	C	C	A	X	A	C	A	X
Methyl Methacrylate	D	B	A	D	X	D	D	D	D	X	A	A	B	B	C	A	X
Methyl Oleate	D	C	A	D	X	D	X	B	A	X	X	A	X	X	X	X	X
Methyl Propyl Salicylate	D	B	A	D	X	D	X	B	B	X	B	A	B	A	A	X	X
Methylamine	X	A	A	B	X	X	X	A	X	X	X	A	C	B	A	A	B
Methylene Bromide	D	X	A	D	X	D	X	D	C	X	X	X	A	D	A	A	A
Methylene Chloride	C	D	A	D	D	D	D	C	B	C	D	A	B	D	B	A	A
Methylene Dichloride	D	X	A	D	X	D	D	D	B	X	X	X	X	X	X	X	X
Milk	A	A	A	A	B	A	D	A	A	A	A	A	A	A	D	A	A
Mine Water	A	B	A	A	X	C	D	A	A	A	A	A	A	A	A	A	A
Mineral Oil	A	D	A	A	A	A	A	D	A	A	B	A	A	A	A	A	A
MLO-7277 Hydr.	X	X	A	C	X	D	D	D	A	X	X	X	X	X	X	X	X
MLO-75557	X	X	A	C	X	D	D	D	A	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytre	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
MLO-8200 Hydr.	X	X	A	B	X	A	A	D	A	X	X	X	X	X	X	X	X
MLO-8515	X	X	A	B	X	B	D	D	A	X	X	X	X	X	X	X	X
Molasses	A	A	A	A	B	A	B	A	A	A	A	B	A	A	A	A	X
Monochloroacetic Acid	D	D	A	D	D	A	D	C	B	D	A	B	A	D	D	D	B
Monochlorobenzene	D	D	A	D	C	D	D	D	A	B	D	A	A/150	D	A	A	X
Monochlorodifluoro Methane	D	D	A	D	D	A	D	A	D	X	A	X	A	A	A	A	X
Monoethanolamine	D	A	A	B	D	B	D	B	D	X	D	D	D	B	A	A	X
Monomethylaniline	D	B	A	D	D	D	D	D	B	A	X	X	X	X	X	X	X
Monomethylether	A	C	A	A	D	B	X	A	A	X	X	X	X	X	X	X	X
Monomethyl Hydrazine	B	X	A	B	D	B	X	A	X	A	X	X	X	X	X	X	X
Mononitrololuene & Dicitrotoluene (40/60 Mixture)	A	X	A	D	D	D	D	D	C	X	X	X	X	X	X	X	X
Muriatic Acid (10%-20% HCL)	B	A	A	D	D	D	B	A	A	A	A	D	A	D	D	D	A
Mustard	B	A	A	B	B	A	B	A	A	A	A	A	X	B	X	A	A
Napalm	B	X	X	B	D	X	B	D	A	X	X	X	X	X	X	X	X
Naptha	A	C	A	A	A	D	C	D	A	A	C	A	A	A	B	A	A
Naptha-Coal Tar (Benzol)	D	C	A	D	D	D	B	D	A	A	C	A	A	A	A	A	A
Napthalene (Tar Camphor)	D	C	A	D	B	D	B	D	A	A	B	A	A	B	A	A	A
Napthenic Acid	B	B	A	B	D	D	X	D	A	X	X	A	X	B	B	A	B
Natural Gas	A	C	A	A	B	A	C	D	A	X	A	A	X	A	A	A	X
Neatsfoot Oil	A	B	A	A	D	D	A	B	A	X	X	B	X	A	A	A	X
Neohexane	A	X	A	A	D	X	X	X	A	X	X	X	X	X	X	X	X
Neosol	A	X	A	A	D	A	X	X	C	X	X	X	X	B	B	A	A
Neville Acid	D	A	A	D	D	D	X	B	A	X	X	X	X	X	X	X	X
Nickel Acetate	B	A	A	B	X	B	D	A	D	X	A	X	A	B	X	A	X
Nickel Ammonium Sulfate	C	A	A	X	X	A	X	X	A	X	X	X	X	X	X	X	X
Nickel Chloride	A	A	A	A	D	B	A	A	A	A	A	B	A	D	D	B	A
Nickel Nitrate	A	A	A	A	X	A	A	A	A	A	A	D	A	D	X	A	B
Nickel Salts	A	A	A	A	X	B	A	A	A	X	X	X	X	X	X	X	X
Nickel Sulfate	A	A	A	A	D	A	A	A	A	A	A	A	A	D	D	A	B
Nicotine	A	X	A	X	B	C	A	X	A	X	X	X	X	X	X	X	X
Nicotinic Acid	A	X	A	A	X	A	X	A	X	X	X	X	X	X	X	X	X
Niter Cake	A	A	A	A	X	A	A	A	A	A	X	X	X	X	X	X	X
Nitrana (Ammonia Fertilizer)	B	X	A	B	X	B	X	X	C	X	X	X	X	X	X	X	X
Nitric Acid																	
Concentrated	D	C	A	D	D	D	D	D	A	D	D	C	A/125	D	D	A	B
Red Fuming (RFNA)	X	D	A	D	D	D	D	D	B	D	D	C	D	D	D	A	B/70
5% To 10% Solution	A	A	A	D	B	D	C	B	A	A	A/120	C	A/120	D	D	A	A
20% Solution	B	B	A	D	D	D	C	B	A	A	B/70	C	A	D	D	A	B
50% Solution	C	C	A	D	D	D	C	D	A	C	B/70	C	A/125	D	D	A	A
65% Solution	D	C	A	D	D	D	C	D	A	D	D	D	A	D	D	A	D
Nitrobenzene	D	B	A	D	D	D	D	C	A	A/70	B/70	B	A/70	C	C	B	B
Nitroethane	D	A	A	D	X	C	D	B	D	A	C	B	X	A	A	A	A
Nitrogen	A	A	A	A	B	A	A	A	A	X	A	A	A	A	A	A	A
Nitrogen Tetroxide	D	D	A	D	B	D	D	D	D	A	D	X	C	D	D	A	A
Nitroglycerine	X	A	A	A	D	A	A	A	A	X	X	X	X	X	X	X	X
Nitromethane	D	A	A	D	D	C	D	B	D	A	C	X	A/120	A	A	A	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrek	Neoprene	Urethane	EPR, Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Nitropropane	X	B	A	D	X	D	D	B	D	A	X	X	X	A	A	A	A
Nitrous Acid	D	X	A	D	X	X	X	B	A	X	D	X	A	D	D	B	A
Nitrous Oxide	A	X	A	A	X	B	B	A	A	X	A	X	D	B	B	D	B
Octachloro Toluene	D	X	A	D	X	D	D	D	A	X	D	X	X	D	X	X	X
Octadecane	X	B	A	A	X	B	A	D	A	X	X	X	X	X	X	X	X
N-Octane	D	B	A	B	X	D	D	D	A	X	D	X	A	X	X	X	X
Octyl Acetate	D	X	A	D	X	X	X	X	D	X	X	X	X	A	X	A	X
Octyl Alcohol	B	X	A	B	X	B	D	B	B	X	X	X	X	X	X	X	X
Oils, Crude (Asphalt Base)	B	D	A	B	B	C	A	D	A	B	B	A	A	A	B	A	A
Oleic Acid (Red Oil)	D	B	A	A	A	C	B/70	C	A	A/122	A	A	A	A	B	A	A
Olein (Triolein)	X	D	A	B	X	C	X	X	X	X	X	X	X	X	X	X	X
Oleum (Fuming Sulfuric Acid)	D	D	A	D	D	D	D	D	B	X	D	D	D	D	D	A	D
Oleum Spirits	D	D	A	B	B	D	C	D	A	A	D	X	D	D	D	B	X
Olive Oil	D	B	A	A	X	B	A	B	A	A	A	A	B	A	A	B	A
Oronite 8200	X	X	A	B	B	A	A	D	A	X	X	X	X	X	X	X	X
Oronite 9515	X	X	A	B	X	X	X	X	X	X	X	X	X	X	X	X	X
Orthochloro Ethyl Benzene	X	X	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Ortho-Dichlorobenzene	X	D	A	D	D	D	D	D	A	X	X	X	X	X	X	X	X
OS 45 Type 111 (OS45)	X	X	A	B	C	A	D	D	B	X	X	X	X	X	X	X	X
OS 45 Type IV (OS45-1)	X	X	A	B	X	A	D	D	B	X	X	X	X	X	X	X	X
OS 70	X	X	A	B	X	A	D	D	A	X	X	X	X	X	X	X	X
Oxalic Acid - 5% (Hot and Cold)	C	A	A	B	D	B	A	A	A	A/140	A	D	A/120	B	D	B	B
Ozone	X	A	A	D	C	C	A	A	A	B	D	D	A	B	X	X	X
Paint Thinner, Duco	D	C	A	D	X	D	D	D	B	X	D	A	X	A	A	A	X
Palmitic Acid	A	B	A	A	A	B	A	B	A	X	A	A	A	C	C	A	B
Palm Oil	X	B	A	A	X	D	A	D	A	A	X	A	A	A	A	A	X
Para-Dichlorobenzene	X	X	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Paraffin	A	A	A	A	X	B	A	D	A	A/70	A	A	A	A	X	A	B
Paraformaldehyde	X	X	A	B/70	X	B	X	A	C/70	X	X	X	X	A	A	A	A
Paraldehyde	X	X	A	D	X	D	X	A	D	X	X	X	X	A	A	A	A
Peanut Oil	A	B	A	A	X	A	B/70	C/70	A	A	A	X	A	X	A	A	A
Pentachloroethane (Pentalin)	D	X	A	D	X	D	X	X	A	X	D	A	A	D	A	A	A
Pentachlorophenol (PCP)	X	X	A	D	X	D	D	D	A	X	X	X	X	A	A	A	A
Pentane	X	X	A	A	X	B	D	D	A	A	X	A	A	A	B	B	B
Peppermint Oil	X	C	X	D	X	D	X	X	A	X	X	X	X	X	X	A	X
Perchloric Acid	D	D	A	D	D	B	D	B	A	A/140	X	C	A/120	D	D	B	X
Perchloroethylene (Tetrachloroethylene)	D	D	A	D	D	D	D	D	B	B	D	A	A	D	B	A	B
Permachlor (Degreasing Fluid)	X	X	A	D	X	X	X	D	C	X	X	X	X	X	X	X	X
Petrolatum	A	X	A	A	X	B	D	D	A	X	A	A	A	B	X	A	A
Petroleum Ether	A	X	A	A	X	D	B	D	A	A	A	A	B	B	B	A	D
Petroleum Oils (Refined)	B	C	A	A	A	B	B	D	A	A	B	A	A	X	X	X	X
Petroleum Oils (Sour)	C	C	A	B	B	B	B	D	A	A	B	A	A	B	B	A	A
Petroleum Oil, Crude	C	C	A	A	A	B	A	D	A	A	B	A	A	X	X	X	X
Phenol	D	A	A	D	D	D	D	X	A	C	C	A	A/70	B	D	A	A
Phenol Sulfonic Acid	X	X	A	D	X	X	X	X	D	X	X	X	AB/120	B	B	B	A
Phenyl Acetate	X	X	A	D	X	D	D	B/70	D	X	X	X	X	X	X	X	X
Phenylbenzene	X	C	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hydrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Phenyl Hydrazine	X	B	A	D	X	D	X	D	A	X	X	X	D	A	D	X	X
Phorone (Diisopropylidene Acetone)	X	B	A	D	X	D	D	B	D	A	X	X	X	X	X	X	X
Phosphate Esters	X	X	A	D	X	D	D	A	D	X	X	X	X	X	X	X	X
Phosphoric Acid 20% 40-100% Solution	X	A	A	B	X	A	C	A	A	A	A	D	A	D	D	A	A
Phosphorous Oxychloride	X	X	A	X	X	D	X	X	X	X	X	X	X	B	B	B	B
Phosphorous Trichloride Acid	D	B	A	D	X	D	X	A	A	A	D	D	A	D	B	A	X
Photographic Developer	B	A	A	A	D	A	B	B	A	A	A	A	A	C	D	A	A
Phthalic Acid	D	X	A	C	X	C	X	A	A	A/70	A	X	A	B	A	B	B
Phthalic Anhydride	X	X	A	C	X	A	X	A	A	X	X	X	X	X	X	X	X
Pickling Solution	D	A	A	D	D	D	C	C/70	B/70	X	X	D	X	X	X	X	A
Picric Acid	B	B	A	D	D	C	C	C	A	X	B/70	D	A/70	C	D	D	D
Pinene	B	C	A	B	D	D	D	D	A	A	X	X	X	X	X	X	X
Pine Oil	B	C	A	B	D	D	D	D	A	C	X	X	X	A	B	A	X
Piperidine	X	B	A	D	D	D	D	D	D	X	X	X	X	X	X	X	X
Pitch	A	X	A	A	D	D	D	D	A	X	X	X	X	X	X	X	X
Plating Solutions																	
Antimony	B	A	A	A	X	A	X	X	A	A	A	A	A	D	A	A	A
Arsenic	B	A	A	A	X	A	X	X	A	A	A	A	X	C	A	A	A
Brass	B	A	A	A	X	A	X	A	A	A	A	A	A	C	A	A	A
Bronze	B	A	A	A	X	A	X	A	A	A	A	B	X	C	A	A	A
Cadmium	B	A	A	A	X	A	X	A	A	A	A	C	A	C	A/70°	A/140°	A/90°
Chrome	D	A	A	D	X	D	X	A	A	A	A	D	A	C	C	A	B
Copper	B	A	A	A	X	A	D	A	X	A	A	X	A	C	A/70°	A/150°	A/120°
Gold	B	A	A	A	X	A	X	A	A	A	A	X	A	C	X	A/150°	A/70°
Indium	B	A	A	A	X	A	X	X	A	A	A	X	X	C	X	A	A
Iron	B	A	A	A	X	A	X	X	A	A	A	X	A	C	X	A	A
Lead	C	A	A	B	X	A	X	A	A	A	A	A	A	C	X	X	X
Nickel	B	A	A	A	X	A	X	A	A	A	A	X	A	C	X	A/70°	A/140°
Silver	B	A	A	A	X	A	X	A	A	A	A	X	A	C	X	A	A
Tin	B	A	A	B	X	A	X	A	A	A	A	X	A	C	X	A	A
Zinc	B	A	A	A	X	A	X	A	A	A	A	X	A	C	X	A	A
Polyvinyl Acetate Emulsion	B	A	A	A	X	B	X	A	D	X	B/70	A	A	X	B	X	X
Potassium Acetate	B	A	A	B	X	B	D	A	D	A	A	A	A	D	A	B	B
Potassium Bicarbonate	A	A	A	A	X	A	D	A	A	A	A	A	A	C	A	B	B
Potassium Bisulfite	A	X	A	A	X	A	A	A	A	X	A	X	X	X	X	X	X
Potassium Bromide	A	A	A	A	X	A	D	A	A	A	A	A	A	C	D	A	A
Potassium Carbonate (Potash)	A	A	A	A	D	A	D	A	A	A	A	A	A	C	B	A	B
Potassium Chlorate	A	A	A	A	X	A	A	A	A	A	A	A	A	B	C	A	B
Potassium Chloride	A	A	A	A	D	A	A	A	A	A	A	A	A	B	B	C	B
Potassium Chromate	A	A	A	A	X	A	B	A	A	A	A	D	A	A	A	B	A
Potassium Cupro Cyanide	X	A	A	A	X	A	X	B	A	X	A	C	A	X	X	X	X
Potassium Cyanide	A	A	A	A	B	A	A	A	A	A	A	C	A	D	B	A	B
Potassium Dichromate	A	A	A	A	B	A	B	A	A	A	A	D	A	A	B	A	B
Potassium Ferricyanide	X	X	A	C	X	A	X	A	A	A	A	B	A	B	C	B	B
Potassium Hydroxide (Caustic Potash)(Lye)	A	A	A	B	A	B	B	A	B	A	A	A	A/150	D	C	A	B
Potassium Hypochlorite	B/70	X	B	B/70	X	B	B	A	D	X	D	D	A	D	D	D	B

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Potassium Iodide	B	X	A	A	X	A	X	A	A	B	A	X	A	B	X	B	B
Potassium Nitrate	A	A	A	A	X	A	A	A	A	A	A	B	A	A	B	B	B
Potassium Permanganate	D	A	A	B	D	A	B	A	A	X	B	C	A	B	B	B	A
Potassium Phosphate	X	X	A	A	X	A	C	A	A	X	X	X	X	D	D	B	B
Potassium Salts	A	X	A	A	X	A	A	A	A	X	X	X	X	X	X	X	X
Potassium Sulfate	A	A	A	A	B	A	A	A	A	A	A	B	A	B	B	A	A
Potassium Sulfide	A	X	A	A	X	A	A	A	A	X	A	X	A	D	B	B	B
Potassium Sulfite	A	X	A	A	X	A	A	A	A	X	A	X	A	A	D	B	X
Potassium Triphosphate	A	X	D(A)	A	X	A	B	X	A	X	X	X	X	X	X	X	X
PRL-High Temp. Hydr. Oil	B/70	X	A	B/70	X	B	B	D	A	A	X	X	X	X	X	X	X
Producer Gas	X	X	A	A	X	B	A	D	A	D	X	A	X	X	X	X	X
Propane (LPG)	B	C	A	A	B	B	B	D	A	C	D	A	A	A	B	A	A
Propane (Liquified)	B	X	A	A	B	B	B	D	A	C	B/70	A	B/20	A	A	A	A
Propane Propionitrile	X	X	A	A	X	B	D	D	A	A	X	X	X	X	X	X	X
Propionadehyde (Propanol)	X	X	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Propionic Acid	X	A	A	D	X	D	D	A	D	X	X	X	X	A	A	A	A
Propyl Acetate	D	B	A	D	X	D	D	B	D	X	C	A	A/70	A	X	A	A
Propyl Alcohol	B	A	A	A	X	A	D	A	A	A	A	A	A	A	A	A	A
Propylene	X	B	A	D	X	D	D	D	A	A	A	A	A	A	A	A	A
Propylene Dichloride	X	X	A	D	X	D	D	D	A	X	X	X	X	D	A	A	B
Propylene Glycol	A	A	A	A	X	C	B	A	A	A	A	D	A	A	B	A	B
Propylene Oxide	D	A	A	D	X	D	D	B	D	A	A/70	A	D	B	B	A	X
Propyl Nitrate	X	B	A	D	X	D	D	B	D	X	C	A	D	B	B	A	X
Pryanol, Transformer Oil	X	X	A	A	X	D	B	D	A	C	X	X	X	X	X	X	X
Pydraul	X	X	X	X	X	X	X	X	X	X	X	X	X	X	A	A	A
Pyridine	X	A	A	D	C	D	D	B	D	D	C	B	D	B	A	B	A
Pyrogalllic Acid	X	X	A	D	X	A	D	B	A	C	X	D	A	X	D	A	B
Pyroligneous Acid	D	X	A	D	X	D	D	B	D	B/70	A	D	A	B	D	A	X
Pyrolube	X	A	A	D	X	D	D	B	A	X	X	X	X	X	X	X	X
Pyrrole	X	C	A	D	X	D	X	D	D	X	X	X	X	X	X	X	X
Quarternary Ammonium Salts	X	X	A/70	A	X	A	X	X	A	X	X	X	X	X	X	X	X
Quench Oil	X	X	A/70	A	X	D	A	D	A	X	X	X	X	A	X	A	A
Quinine Bisulphate (Dry)	D	X	A	A	X	A	A	A	A	A	D	D	D	D	D	B	A
Quinine Sulphate (Dry)	D	X	A	A	X	A	A	A	A	A	D	D	D	D	D	A	A
Radiation	X	X	A	B	X	C	B	C/70	D	X	X	D	X	X	X	X	X
Rape Seed Oil	X	B	A	B	X	B	B/70	A	A	D	X	X	X	X	A	A	A
Red Line 100 Oil	X	X	X	A	X	B	A	D	A	X	X	X	X	X	X	X	X
RJ-1 (Mil-F-25558)	X	X	X	A	X	B	B	D	A	A	X	X	X	X	X	X	X
RP-1 (Mil-R-25576)	X	X	X	A	X	C	C	D	A	A	X	X	X	X	X	X	X
Rose Oil	X	A	X	X	X	C	A	X	A	X	X	X	X	X	X	A	X
Rosins	A	A	A	A	X	A	D	D	A	D	A	B	X	A	D	A	A
Rosin Paper Mill	X	A	A	A	X	A	D	A	A	D	A	B	X	A	D	A	A
Rotenone	X	X	A	A	X	A	X	A	A	X	X	X	X	X	X	X	X
Rum	A	A	A	A	X	A	D	A	A	X	A	A	X	X	X	A	A
Rust Inhibitors	A	B	X	A	X	C	A	X	A	X	A	A	X	X	C	A	X
Sal Ammoniac	X	A	A	A	A	A	A	A	A	A	A	D	A	D	D	B	A
Sal Soda	A	B	A	A	X	A	X	A	A	X	X	X	X	D	A	A	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Salad Dressing	D	A	X	D	D	D	D	D	D	X	A	A	X	B	D	A	X
Salicylic Acid	A	A	A	A	X	D	X	A	A	A	A	X	A	A	D	B	A
Santo Safe 300	X	X	A	D	B	D	X	C/70	A	A	X	X	X	X	X	X	X
Salt Water	A	A	A	A	X	A	D	A	A	A	A	A	A	D	D	C	A
Sea Water	A	A	A	A	A	A	A	A	A	A	A	A	A	D	D	C	A
Sesame Seed Oil	A	B	X	A	X	C	X	X	A	X	X	X	X	X	A	A	X
Sewage	A	A	A	A	A	A	D	A	A	A	A	A	A	B	B	A	A
Shellac	A	A	A	A	D	D	D	A	A	D	A	A	X	A	A	A	A
Silicate Esters	A	B	A	A	C	A	B	D	A	D	X	X	X	X	X	X	X
Silicone Greases	A	B	A	A	A	A	A	A	A	A	X	A	X	X	X	X	X
Silicone Oils	A	C	A	A	B	A	A	A	A	A	A	A	A	B	A	A	A
Silicone Tetrachloride Wet	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Silver Bromide	X	X	A/70	X	X	X	X	X	X	X	X	A	X	D	D	B	A
Silver Chloride	D	X	A/70	X	X	X	X	X	X	X	A	X	X	X	X	X	X
Silver Cyanide	A	X	A	A	X	A	D	A	A	A	A	X	A	D	A	A	A
Silver Nitrate	C	A	A	B	D	A	A	A	A	A	A	A	A	D	D	A	A
Spelly, Solvent B ,C, E	X	X	A	A	X	D	X	D	A	X	X	X	X	X	X	X	X
Skydrol 500	D	B	A	D	A	D	D	A	D	X	X	A	X	X	X	A	A
Skydrol 7000	X	B	A	D	D	D	D	A	B/70	X	X	A	X	X	X	A	A
Soap Solutions	A	A	A	A	A	A	A	A	A	A/70°	A	A	A	C	D	A	A
Sodium Acid Sulfate	A	A	A	A	X	A	A	A	A	A	A	X	X	X	B	X	X
Sodium Aluminate	A	A	A	A	X	A	X	A	A	X	A	A	A	C	A	A	A
Sodium Aluminium Sulfate	A	A	A	A	X	A	A	A	A	X	X	X	X	X	X	X	B
Sodium Bicarbonate	A	A	A	A	B	A	A	A	A	A/70	A	A	A	A	C	A	B
Sodium Bichromate	B	A	A	A	X	A	A	A	A	A	A	D	A	C	C	B	C
Sodium Bisulfate	A	A	A	A	AC	A	A	A	A	A	A	A	A	D	D	A	B
Sodium Bisulfite	A	A	A	A	B	A	A	A	A	A	A	A	A	A	D	A	A
Sodium Borate (Borax)	A	A	A	A	B	A	A	A	A	A/70°	A/140	A	A	C	B	B	A
Sodium Bromide	X	A	A	X	X	A	X	A	A	X	A	X	A	C	C	B	B
Sodium Carbonate	A	A	A	A	B	A	A	A	A	A	A	A	A	C	B	A	A
Sodium Chlorate	A	A	A	A	X	A	A	A	A	A	A	A	A	B	B	A	A
Sodium Chloride	A	A	A	A	A	A	A	A	A	A	A	A	A	C	B	C	A
Sodium Chromate	A	A	A	A	X	A	X	X	A	X	A	D	A	A	A	A	A
Sodium Citrate	D	A	X	X	X	X	X	X	X	A	X	X	X	X	X	B	A
Sodium Cyanide	A	A	A	A	B	A	A	A	A	A	A	B	A	D	B	A	A
Sodium Dichromate	A	A	A	A	B	B	B	A	B	A/140	A	X	A	X	X	X	X
Sodium Ferricyanide	A	A	A	A	X	A	X	A	A	A	A	X	A	A	D	B	B
Sodium Fluoride	A	A	A	A	X	A	B	A	A	A	A	X	A	B	X	B	B
Sodium Hydroxide																	
20% (Cold)	B	A	A	A	A	B	B	A	A	A	A	A	A	D	B	A	B
50% Solution (Cold)	D	A	A	D	B	C	B	A	A	A	A	A	C	D	C	B	A
80% Solution (Cold)	D	X	A	D	D	C	B	A	A	A	A	A	C	D	C	D	B
Sodium Hydrosulfate	X	X	X	X	X	X	X	X	X	A	X	X	X	X	X	X	X
Sodium Hypochlorite 0-20%	D	B	A	D	C	B	D	B	C	A	B	D	A	D	D	C	A
Sodium Metasilicate	A	A	A	A	X	A	B/70	A	A	X	A	B	A	B	X	A	A
Sodium Nitrate	C	A	A	A	B	B	B/70	A	A	A	A	A	A	A	A	A	A
Sodium Perborate	B	A	A	B	B	B	B/70	A	A	A/70	A	B	A	D	B	A	B

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Sodium Peroxide (Sodium Dioxide)	B	B	A	B	B	B	D	A	A	A/140	B	D	A	B	A	B	B
Sodium Phosphate	A	A	A	A	C	A	A	A	A	A/70	A	A	A	D	B	B	A
Sodium Phosphate (Mono)	A	A	A	A	B	C	A	A	A	X	A	A	A	D	D	A	X
Sodium Phosphate (Dibasic)	B	A	A	A	B	B	A	A	A	X	A	A	A	D	D	A	X
Sodium Phosphate (Tribasic)	B	A	A	A	B	C	A	A	A	X	A	A	A	D	D	A	A
Sodium Silicate (Water Glass)	A	A	A	A	B	A	B	A	A	A	A	C	A	C	B	A	B
Sodium Sulfate (Salt Cake)	A	A	A	A	B	A	A	A	A	A	A	B	A	B	A	A	B
Sodium Sulfide	A	A	A	A	B	A	A	A	A	A/70	A	B	A	D	A	A	B
Sodium Sulfide - Saturated	A	A	A	A	B	A	A	B	B	A	A	A	A	D	B	B	A
Sodium Sulfite	A	A	A	A	B	A	A	A	A	A	A	A	A	A	D	A	B
Sodium Tetraborate	B	A	A	A	B	A	B	A	A	A/70	A	A	A	A	B	A	B
Sodium Tetraphosphate	X	A	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X
Sodium Thiosulfate (Antichlor)	A	A	A	X	X	X	X	X	X	A	A	B	A	A	C	A	B
Sodium Triphosphate	X	X	A	A	B	A	A	A	A	X	A	C	A	B	C	A	A
Sorghum	A	A	X	A	X	A	X	X	A	X	X	A	X	X	A	A	A
Soybean Oil	A	C	A	A	B	A	B/70	D	A	A	B	B	X	A	A	A	A
Soy Sauce	A	A	X	A	X	A	B	X	A	X	X	A	X	A	D	A	X
Sperm Oil (Whale Oil)	X	B	X	A	X	D	X	D	A	X	X	X	X	X	A	A	A
Spry	X	X	X	A	X	B	A	B/70	A	A	X	X	X	X	X	X	X
SR-6 Fuel	X	X	X	B/70	X	D	B/70	D	A	A	X	X	X	X	X	X	X
SR-10 Fuel	X	X	X	A	X	D	B/70	D	A	A	X	X	X	X	X	X	X
Stannic Chloride	A	A	A	A	B	C	B	A	A	A	A	B	A	D	D	D	B
Sannic Fluorborate	X	X	X	A	X	A	X	X	A	X	X	C	X	D	D	X	X
Stannous Chloride	A	B	A	A	B	A	C	B	A	X	A	X	A	D	B	A	A
Starch	A	A	A	A	B	A	A	A	A	A	A	B	X	A	C	A	A
Stearic Acid	B	A	A	B	B	B	A	B	A	A	B/72	A	A	B	X	A	A
Stoddard Solvent	B	D	A	A	C	D	A	D	A	X	A/70	A	A	A	A	A	A
Styrene (Vinyl Benzene)	D	C	A	D	D	D	D	D	B	A	D	A	A	A	B	A	D
Sucrose Solutions (Sugar)	A	A	A	A	B	A	A	A	A	A	X	A	X	A	B	A	A
Sugar Liquids	A	A	A	A	B	A	D	A	A	A	A	A	A	A	A	A	A
Sulfate Black Liquor	B	A	A	B	B	A	A	A	A	A	A	D	A	B	C	A	A
Sulfate Green Liquor	B	A	A	B	B	A	A	A	A	A	A	D	A	B	C	A	A
Sulfite Liquor	B	A	A	B	X	A	C	B/70	A	A	B	X	X	D	D	B	A
Sulfur	B	A	A	B	X	B	B	A	A	A	A	A	A	A	A	A	B
Sulfur Chloride	D	D	A	D	C/70	A	C/70	D	A	A	C	D	A/70	B	D	B	A
Sulfur Dioxide	D	A	A	D	D	A	C	A	A	A	A	D	A	D	D	A	B
Sulfur Hexafluoride	C	B	A	B/70	B	B	B	A	C	A	X	D	X	D	D	X	D
Sulfur Trioxide	D	D	A	D	D	A	C	C	A	C	D	X	C	D	D	B	B
Sulfuric Acid -Dilute	D	A	A	D	A	C	C	A	A	A	A	D	A	D	D	B	A
Sulfuric Acid - (To 10%)	D	A	A	D	A	D	D	A	A	A	A/120	D	A	D	D	C	A
Sulfuric Acid - (To 75%)	D	A	A	D	B	D	D	C	A	X	A/72	D	A/150	D	D	C	B
Concentrated	D	B	A	D	C	D	D	C	A	X	C/72	D	A/120	D	D	B	A
(Fuming) Oleum	D	A	A	D	B	D	D	B	A	X	D	D	D	C	D	B	B
Sulphurous Acid	D	X	A	D	D	D	D	D	D	A	A	D	A	D	D	B	B
Sunsafe (Fire Resist. Hydr. Fluid)	B	D	A	A	A	B	D	D	A	X	X	X	X	X	X	X	X
Syrup	A	A	X	A	X	B	X	A	A	X	A	A	X	A	X	A	X
Tall Oil	A	D	A	A	X	D	A	D	A	X	A	X	A	D	C	B	A

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Tallow	B	B	A	A	X	D	A	A	A	A/70	B/70	A	X	A	X	A	X
Tannic Acid	A	A	A	A	A	A	A	A	A	A	A	D	A	D	C	A	B
Tanning Oils	X	X	A	A	X	D	X	X	A	X	A	D	A	A	X	A	A
Tar and Tar Oil	X	X	A	X	C	C	D	X	X	C	A	A	A	A	C	B	X
Tar, Bituminous	B	B	A	B/70	B	C	B/70	D	A	X	A	A	X	A	X	A	A
Tartaric Acid	B	A	A	A	(B)	A	A	C	A	A	A	D	A	A	D	A	A
Terpene Monocyclic	X	X	A	C/70	X	A	X	D	A	X	X	X	X	A	D	X	X
Terpineol	D	B	A	B/70	X	D	B/70	C/70	A	X	D	X	B/120	A	A	A	A
Tertiary Butyl Alcohol	D	B	A	B	X	B	D	B/70	A	X	B	A	X	X	X	X	X
P-Tertiary Butyl Catechol	X	B	A	D	X	B	X	B/70	A	X	X	A	X	C	B	B	X
Tertiary Butyl Mercaptan	X	B	A	D	X	D	D	D	A	X	X	B	X	X	X	X	X
Terta Bromoethane	D	D	A	D	X	D	X	D	A	X	D	X	X	D	X	X	X
Tetrabutyl Titanate	X	B	A	B/70	X	B	X	A	A	X	X	X	X	X	X	X	X
Tetrachlorodifluorethane	D	D	A	B	X	D	X	D	X	X	X	X	X	X	X	X	X
Tetrachloroethylene	D	D	A	D	X	D	D	D	A	B/70	D	A	A/170	D	A	A	X
Tetraethyl Lead	B	C	A	B	B	C	B	D	A	C	A	X	A	B	A	A	X
Tetraethylene Glycol	X	X	A	A	X	X	X	X	A	X	X	X	X	X	X	X	X
Tetrahydrofuran	D	B	A	D	B	D	D	D	D	B/70	C	A	B/70	X	X	A	A
Tetralin	D	C	A	D	X	D	D	D	A	X	D	X	X	A	A	A	A
Thiokol TP-90B	X	X	X	D	X	B	X	A	A	X	X	X	X	X	X	X	X
TP-95	X	X	X	D	X	B	X	A	A	X	X	X	X	X	X	X	X
Thionyl Chloride	X	X	X	X	X	X	X	X	X	D	B	B	D	C	D	D	A
Thiophene	D	D	A	D	X	D	X	D	C	X	X	X	X	X	X	X	X
Tin Tetrachloride	A	X	A	A	X	D	B/70	X	X	X	A	X	A	D	D	D	A
Titanium Tetrachloride	C	D	A	B	X	D	D	D	A	C	D	X	B	D	A	B	B
Toluene (Toluol)	C	D	A	D	C	D	D	D	B	C	D	A	A	A	A	A	A
Toluene Di-isocyanate (Hylene)	X	B	A	D	B	D	X	A	C	X	X	C	X	X	X	X	X
Toluidine	X	X	A	D	X	X	X	X	B/70	X	X	X	X	A	A	A	A
Tomato Pulp & Juice	A	A	A	A	X	A	A	A	A	A	A	A	A	B	X	A	A
Transformer Oils	B	D	A	A	X	B	A	D	A	A/70	B/70	A	A	A	A	A	A
Transmission Fluid, Type A	X	C	A	A	B	B	A	D	A	X	X	A	X	A	A	A	A
Triacetin	X	A	A	B	X	B	D	A	D	X	X	X	X	B	X	X	X
Triaryl Phosphate	D	X	A	D	X	D	D	A	A	A	B	X	A	X	X	X	X
Tributoxyl Ethyl Phosphate	X	B	A	D	X	D	D	A	A	A	X	X	X	X	X	X	X
Tributyl Mercaptan	X	B	A	D	X	D	X	D	A	A	X	X	X	X	X	X	X
Tributyl Phosphate	D	B	A	D	C	D	D	B	D	D	B	X	A	A	A	A	X
Trichloroacetic Acid	D	B	A	D	D	D	D	B/70	D	X	B/140	D	A/70	D	D	D	B
Trichlorobenzenes	X	X	A	D	X	D	D	X	A	X	X	X	X	D	A	A	B
Trichloroethane	D	D	A	D	D	D	D	D	A	D	D	A	B/150	D	A	A	A
Trichloroethylene (Triad)	D	D	A	D	D	D	D	D	C	X	C/70	B	A	B	B	B	B
Trichloromonofluoroethane (Freon 17)	D	X	X	D	X	D	X	X	X	X	X	X	X	A	X	A	A
Trichloropropane	D	D	A	A	X	A	A	X	A	X	D	A	X	D	A	A	A
Trichlorotrifluoroethane (Freon 113)	A	D	A	A	A	A	B	D	A	X	A	X	A	A	A	A	A
Tricresyl Phosphate	D	B	A	D	C	C	D	A	A	A	B	C	D	D	A	A	A
Tridecyl Alcohol (Tridecanol)	X	X	A/170	A	X	X	B	X	B/70	X	X	X	X	X	X	X	X
Triethanol Amine	D	A	A	C	C	A	D	A	D	A/70	A/70	A	A	B	A	A	A
Triethyl Aluminium	X	B	A	D	D	D	X	X	B/70	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	Teflon	Nitrile (TS)	Hytrel	Neoprene	Urethane	EPR,Epdm	Viton	UHMPE	Polypropylene	Acetal	PVDF	Aluminum	Cast Iron	Stainless	Hastelloy
Triethyl Amine	D	D	A	A	X	B	D	A	A	X	C	A	A/120	X	A	A	A
Triethylene Glycol (TEG)	A	X	A	A	X	X	X	X	A	A	A	X	X	X	X	X	X
Triethyl Borane	X	B	A	D	X	D	X	X	A	X	X	X	X	X	X	X	X
Trifluoroethane	X	X	A	D	X	D	D	D	A	X	X	X	X	X	X	X	X
Trimethylene Glycol	X	X	A	A	X	X	X	A	A	X	X	X	X	X	X	X	X
Trinitrotoluene (TNT)	X	A	A	D	X	B	X	D	B/70	X	X	X	X	X	X	X	X
Trioctyl Phosphate	X	B	A	D	X	D	D	A	B	X	X	X	X	X	X	X	X
Triphenyl Phosphate	D	X	A	D	X	X	X	X	C/70	X	X	X	X	X	X	X	X
Trisodium Phosphate	A	A	A	A	A	A	B	A	A	A	A	D	A	D	A	B	A
Tung Oil	D	B	A	A	(B)	A	B	D	A	A	A	X	A	A	B	A	A
Turbine Oil	X	X	A	B	X	B	A	D	A	X	X	X	X	X	X	X	X
Turbine Oil #15 (Mil-L-7808A)	X	X	A	B	X	D	D	D	A	X	X	X	X	X	X	X	X
Turbo Oil #35	X	X	X	A	X	B	A	D	A	X	X	X	X	X	X	X	X
Turpentine	B	D	A	A	B	D	D	D	A	C/70	B/120	A	A	A	B	A	B
Type 1 Fuel (Mil-S-3136)	X	D	A	A	A	A	B	D	A	X	X	X	X	X	X	X	X
Type 11 Fuel (Mil-S-3136)	X	D	A	B	X	D	B/70	D	A	X	X	X	X	X	X	X	X
Type 111 (Fuel Mil-S-3136)	X	D	A	B	A	D	B/70	D	A	X	X	X	X	X	X	X	X
Univis 40 (Hydr. Fluid)	X	D	A	A	X	B	A	D	A	X	X	X	X	X	X	X	X
Univolt #35 (Mineral Oil)	X	C	A	A	X	B	A	D	A	X	X	X	X	X	X	X	X
Unsymmetrical Dimethyl Hydrazine	X	B	A	B/70	X	B	D	A	D	X	X	X	A/70	B	A	A	X
Urea (Carbamide)	B	A	A	B	B	A	B	A	A	A	A	A	A	B	X	B	B
Uric Acid	X	X	A	X	D	X	D	X	X	X	D	D	D	D	X	B	B
Urine	A	A	A	A	X	D	X	A	A	A	A	C	A	B	B	A	A
Valeric Acid	X	X	A	D	X	D	X	A	X	X	X	X	X	A	X	X	X
Vanilla Extract	X	A	A	A	X	A	X	X	X	X	X	X	X	X	X	A	X
Varnish	B	D	A	B	X	D	B	D	A	A/70	A	X	A	A	X	A	A
Vegetable Juices	X	A	D	A	X	B	B	A	A	X	X	A	X	C	X	A	X
Vegetable Oil	A	A	A	A	X	B	A	A	A	D	A	A	A	A	B	A	A
Versilube	X	X	A	A	X	A	A	A	A	A	X	X	X	X	X	X	X
Versilube F-50	X	X	A	A	X	A	A	A	A	A	X	X	X	X	X	X	X
Vinegar	B	A	A	B/70	C	B	B	A	A	A	A	B	A	D	C	A	A
Vinyl Acetate	D	B	A	D	X	D	D	B	A	D/70°	B/80	X	A	B	A	A	A
Vinyl Chloride (Chloroethylene)	X	X	A	D	X	D	X	C	A	X	D	X	A	D	B	A	A
Walnut Oil	X	X	A	A	X	B	X	X	A	X	X	X	X	X	X	X	X
Water, Acid Mine	A	A	A	A	X	C	C	A	A	A	A	A	A	D	D	A	A
Water, Fresh	A	A	A	A	A	A	A	A	B	A	A	A	A	A	B	A	A
Water, Distilled	A	A	A	A	X	B	A	A	A	A	A	A	A	B	D	A	A
Water, Salt	A	A	A	A	A	A	B	A	A	A	A	A	A	D	D	C	X
Water-Brine, Process, Beverage	X	A	D	A	X	A	D	A	A	A	X	X	X	X	X	X	X
Waxes	D	X	A	A	X	A	A	B	A	A	D	A	D	D	D	D	A
Wemco C	X	X	A	A	X	B	A	D	A	X	X	A	X	X	X	A	X
Whey	A	A	X	A	X	X	X	X	A	X	X	X	X	B	X	A	X
Whiskey and Wines	A	A	A	A	B	A	D	A	A	A	A	A	A	D	D	A	A
White Liquor (Pulp Mill)	A	A	A	A	X	A	D	A	A	X	X	X	X	X	X	X	X
White Pine Oil	X	A	A	B/70	D	D	X	D	A	X	X	A	X	X	X	X	X
White Oil	X	C	A	A	X	B	A	D	A	A	X	A	X	X	X	A	A
Wolmar Salt	X	X	A	A	X	B	A	A	A	X	X	X	X	X	X	X	X

Compatibility Guide

A=Excellent, B=Good, C=Fair to Poor, D=Not recommended

Bold Headings = TPE *Italic Headings = TS*

X or Brackets around a rating letter, no data is available, but the ratings are made on the basis of exposure test in similar chemical groups.

MATERIAL	Nitrile (TPE)	Santoprene	<i>Teflon</i>	<i>Nitrile (TS)</i>	Hytrel	<i>Neoprene</i>	<i>Urethane</i>	<i>EPR, Epdm</i>	<i>Viton</i>	<i>UHMPE</i>	<i>Polypropylene</i>	<i>Acetal</i>	<i>PVDF</i>	<i>Aluminum</i>	<i>Cast Iron</i>	<i>Stainless</i>	<i>Hastelloy</i>
Wood Alcohol	X	X	A	A	X	A	D	A	D	A	X	X	X	X	X	X	X
Wood Oil	X	X	A	A	A	B	C/70	D	A	A	X	X	X	A	A	A	X
Wort, Distillery	X	X	X	A	X	B	B/70	A	A	X	X	X	X	A	B	A	A
Xylene (Xylol)	C	D	A	D	B	D	D	A	A	C/70	B	A	A	A	A	A	A
Zeolites	X	A	A	C	X	C	X	A	A	X	X	X	X	X	X	A	A
Zinc Acetate	B	A	A	B	X	B	D	A	B	A	A	X	A	C	X	A	X
Zinc Carbonate	A	A	A	A	X	A	A	A	A	A	X	X	X	B	B	B	B
Zinc Chloride	A	A	A	A	A	A	A	A	A	A	A	D	A	D	D	C	A
Zinc Hydrosulphite	A	A	(A)	A	X	A	X	A	X	X	X	C	A	D	X	A	X
Zinc Salts	A	A	A	A	X	A	A	A	A	X	A	X	A	X	X	X	X
Zinc Sulfate	A	A	A	A	C	A	A	A	A	A	A	C	A	D	D	A	A

NORTH AMERICA

United States

Ingersoll-Rand Fluid Products
P.O. Box 151
One Aro Center
Bryan, Ohio 43506
PHONE: 1 (419) 636-4242
FAX: 1 (419) 633-1674

Canada

Production Equipment Group
Ingersoll-Rand Canada Inc.
51 Worcester Road
Rexdale, Ontario M9W 4K2
PHONE: 1 (416) 213-4500
FAX: 1 (416) 213-4510

LATIN AMERICA

Latin America Headquarters

Ingersoll-Rand PEG Aro Division
730 N.W. 107 Avenue, Suite 300
Miami, FL 33172-3107
PHONE: (305) 222-0812/559-0500
FAX: (305) 222-0864/559-7505

Brazil

Ingersoll-Rand do Brasil Ltda.
Av. Dr. Cardoso de Melo 1855
Cep. 04548-005 São Paulo S.P.
55 11 822 7400
PHONE: (55-11) 822-7400
FAX: (55-11) 866-4985

Chile

Ingersoll-Rand Chile, Ltda.
Nueva Tajamar 555
Oficina 1502
Santiago, Chile
PHONE: 56-2 339-7939
FAX: 56-2 339-7940

Mexico

Ingersoll-Rand, S.A. de C.V.
Blvd. Centro Industrial No.11
Industrial Puente de Vigas
54070 Tlanepantla, Edo. Mex.
PHONE: (525) 3 90 40 21 Ext. 109
FAX: (525) 3 90 40 31

LATIN AMERICA (Cont.)

Venezuela

Ingersoll-Rand Company
Centro Profesional Eurobuilding, Ofic. 6
Chuao 1061, Caracas, Venezuela
PHONE: (58-2) 910867 / 911868
(58-2) 918908 / 927553
FAX: (58-2) 993-9276

EUROPE

European Headquarters

Europe, Africa & Middle East
Ingersoll-Rand
5-7, avenue Albert Einstein
78192 Trappes - France
PHONE: (33) 01 348 22 900
FAX: (33) 01 348 22 901

Germany

Ingersoll-Rand GMBH
PEG Fluid Products Division Gewerbeallee 17
45478 Mulheim-Germany
PHONE: (49) 02 08 99 940
FAX: (49) 02 08 99 94 444

Benelux & France

Ingersoll-Rand
PEG Fluid Products Division
5-7, avenue Albert Einstein
78192 Trappes - France
PHONE: (33) 01 348 22 900
FAX: (33) 01 348 22 901

Ireland, Scandanavia &

United Kingdom

Ingersoll-Rand Co. Ltd.
PEG Fluid Products Division
Swan Lane Works
Swan Lane Hindley Green
Wigan WN2 4EZ, England
PHONE: (44) 01 942 502 167
FAX: (44) 01 942 502 181

Greece, Italy, Morocco, Portugal & Spain

Ingersoll-Rand Co. Italianna S.p.A.
PEG Fluid Products Division
C. so Duca degli Abruzzi, 54
10129 Torino - Italy
PHONE: (39) 011 56 81 594
FAX: (39) 011 56 83 277

ASIA

Japan

Ingersoll-Rand Japan, Ltd.
Shin-Yokohama Square Bldg. 5F
3-12, Shin-Yokohama 2-chome
Kohoku-ku, Yokohama-shi
Kanagawa Pref. 222, Japan
PHONE: (81) 45-476-7801
FAX: (81) 45-476-7806

Singapore

Ingersoll-Rand S.E.A. Pte Ltd.
42, Benoi Road
Singapore 2262
PHONE: (65) 8611555
FAX: (65) 8610317

Australia

Ingersoll-Rand Australia, Ltd.
1 Hartnett Drive
Seaford, Vic 3198
PHONE: (61) 3 9554-1600
FAX: (61) 3 9554-1611

China / Hong Kong

Ingersoll-Rand Hong Kong
Suite 1201-3, 12 Floor, Central Plaza
18 Harbour Road
Wanchai, Hong Kong
PHONE: (852) 2527-0183
FAX: (852) 2529-5976

Korea

Ingersoll-Rand Korea
Production Equipment Group
#1005, 10th Floor, Guhsung Bldg.
541, Dohwa-Dong
Mapo-Ku, Seoul
Korea
PHONE: (82) 2-703-8461 / 3
FAX: (82) 2-3272-5894

Taiwan

Ingersoll-Rand Taiwan
12F-2, No. 79
Shin-Tai Wu Road
Sec. 1, Hsi-Chih Town
Taipei Hsien, Taiwan, R.O.C.
PHONE: 886-2-698-4858 Ext. 18
FAX: 886-2-698-9897

INGERSOLL-RAND

FLUID PRODUCTS

FORM 8677-P
0999

Fluid Products Division Production Equipment Group

Ingersoll-Rand Company
P.O. Box 151 • One Aro Center
Bryan, Ohio 43506-0151
(419) 636-4242 • FAX (419) 633-1674
Fluid Handling: (U.S.A. only)
(419) 633-1794 • FAX (419) 633-1772
Web: www.ingersoll-rand.com